

## SCG Chemicals EL-Pro,ç P401S Polypropylene Flat Yarn/Sheet

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene, Fiber Grade

### Material Notes:

Key Characteristics: Excellent mechanical properties  
Recommended Applications: Stretch tape for jumbo woven sheet  
Monofilament for rope and sheet  
Information provided by SCG Chemicals

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_SCG-Chemicals-EL-Pro-P401S-Polypropylene-Flat-YarnSheet.php](http://www.lookpolymers.com/polymer_SCG-Chemicals-EL-Pro-P401S-Polypropylene-Flat-YarnSheet.php)

Physical Properties	Metric	English	Comments
Specific Gravity	0.910 g/cc	0.910 g/cc	ASTM D1505
Environmental Stress Crack Resistance	>= 500 hour @Temperature 50.0 Å°C	>= 500 hour @Temperature 122 Å°F	F50, 25% Igepal; ASTM D1693
Melt Flow	2.4 g/10 min @Load 2.16 kg, Temperature 230 Å°C	2.4 g/10 min @Load 4.76 lb, Temperature 446 Å°F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	85	85	ASTM D785
Tensile Strength at Break	25.0 MPa	3630 psi	ASTM D638
Tensile Strength, Yield	31.4 MPa	4550 psi	ASTM D638
Elongation at Break	650 %	650 %	ASTM D638
Flexural Modulus	1.397 GPa	202.7 ksi	ASTM D790
Izod Impact, Notched	0.177 J/cm @Temperature -20.0 Å°C	0.331 ft-lb/in @Temperature -4.00 Å°F	ASTM D256
	0.275 J/cm @Temperature 0.000 Å°C	0.514 ft-lb/in @Temperature 32.0 Å°F	ASTM D256
	0.412 J/cm @Temperature 23.0 Å°C	0.771 ft-lb/in @Temperature 73.4 Å°F	ASTM D256

Thermal Properties	Metric	English	Comments
Melting Point	163 Å°C	325 Å°F	ASTM D2117

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (264 psi)	110 Â°C	220 Â°F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	60.0 Â°C	140 Â°F	ASTM D648
Vicat Softening Point	155 Â°C	311 Â°F	ASTM D1525

Optical Properties	Metric	English	Comments
Haze	50 % @Thickness 1.00 mm	50 % @Thickness 0.0394 in	ASTM D1003
Gloss	85 % @Thickness 1.00 mm	85 % @Thickness 0.0394 in	ASTM D2457

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China