

SCG Chemicals EL-Pro, P750J Polypropylene Injection Molding

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene, Molded

Material Notes:

Key Characteristics:Excellent clarityHigh productivityGood processability and stiffnessHigh glossOdorlessSafe for food

contactRecommended Applications:Food container, utensilMedical parts such as syringePremium articles with excellent clarityInformation provided by SCG Chemicals

Order this product through the following link:

http://www.lookpolymers.com/polymer_SCG-Chemicals-EL-Pro-P750J-Polypropylene-Injection-Molding.php

Physical Properties	Metric	English	Comments
Specific Gravity	0.910 g/cc	0.910 g/cc	ASTM D1505
Linear Mold Shrinkage, Flow	0.014 cm/cm @Thickness 2.00 mm	0.014 in/in @Thickness 0.0787 in	TPE Method
Linear Mold Shrinkage, Transverse	0.014 cm/cm @Thickness 2.00 mm	0.014 in/in @Thickness 0.0787 in	TPE Method
Melt Flow	12 g/10 min @Load 2.16 kg, Temperature 230 Â°C	12 g/10 min @Load 4.76 lb, Temperature 446 Â°F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	90	90	ASTM D785
Tensile Strength at Break	22.0 MPa	3190 psi	ASTM D638
Tensile Strength, Yield	29.4 MPa	4270 psi	ASTM D638
Elongation at Break	500 %	500 %	ASTM D638
Flexural Modulus	1.18 GPa	171 ksi	ASTM D790
Izod Impact, Notched	0.392 J/cm @Temperature 0.000 Â°C	0.735 ft-lb/in @Temperature 32.0 Â°F	ASTM D256
	0.686 J/cm @Temperature 23.0 Â°C	1.29 ft-lb/in @Temperature 73.4 Â°F	ASTM D256

Thermal Properties	Metric	English	Comments
Melting Point	150 Â°C	302 Â°F	ASTM D2117

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (264 psi)	90.0 Â°C	194 Â°F	ASTM D648
Vicat Softening Point	130 Â°C	266 Â°F	ASTM D1525
Brittleness Temperature	-20.0 Â°C	-4.00 Â°F	ASTM D746
Flammability, UL94	HB	HB	

Optical Properties	Metric	English	Comments
Haze	12 % @Thickness 1.00 mm	12 % @Thickness 0.0394 in	ASTM D1003
Gloss	77 % @Thickness 1.00 mm	77 % @Thickness 0.0394 in	ASTM D2457

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China