

SGL Carbon Group PANOX® SA C063 SSC High performance oxidized textile fiber, Crimped staple fiber, For felts and non-wovens

Category: Carbon, Carbon Fiber, Other Engineering Material, Composite Fibers

Material Notes:

PANOX® is the industry standard when it comes to fire-retardant textile fibers. As an oxidized, thermally stabilized polyacrylonitrile (PAN) fiber that will not burn, melt, soften or drip, PANOX is ideal for processing into yarns, woven fabrics, nonwovens and felts. Information provided by SGL Carbon Group

Order this product through the following link:

http://www.lookpolymers.com/polymer_SGL-Carbon-Group-PANOX-SA-C063-SSC-High-performance-oxidized-textile-fiber-Crimped-staple-fiber-For-felts-and-non-wovens.php

| Physical Properties | Metric | English | Comments |
|---------------------|------------------|------------------------|---------------|
| Density | 1.39 - 1.43 g/cc | 0.0502 - 0.0517 lb/in³ | Fiber Density |
| Filament Diameter | 15 Âμm | 15 Âμm | |
| Fiber Count | 2.22 dtex | 2.00 denier | |

| Mechanical Properties | Metric | English | Comments |
|---------------------------|----------------|------------------|----------|
| Tensile Strength at Break | 190 MPa | 27600 psi | |
| Elongation at Break | 15 - 27 % | 15 - 27 % | |
| Tenacity | >= 0.140 N/tex | >= 1.59 g/denier | |

| Descriptive Properties | Value | Comments |
|---------------------------|-------|----------|
| Mean Fiber Length, mm | 63 | |
| Typical Finish Content, % | 1 | |

Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058 Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China