

SGL Carbon Group Ridurid® V 1352 High Performance Graphite Filled Plastic

Category : Polymer , Thermoset , Filled/Reinforced Thermoset , Phenolic

Material Notes:

Good mechanical strength, good sliding properties, high temperature resistance, high thermal shock resistance, low wettability, high corrosion resistance, high thermal conductivity, high purity, and good electrical conductivity. Typical Applications: Seals, compressors, pumps, bearings. Information provided by SGL Carbon Group

Order this product through the following link:

http://www.lookpolymers.com/polymer_SGL-Carbon-Group-Ridurid-V-1352-High-Performance-Graphite-Filled-Plastic.php

Physical Properties	Metric	English	Comments
Density	1.64 g/cc	0.0592 lb/in ³	
Open Porosity	0.00 %	0.00 %	

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	105	105	Ball Size/Load - 5/100
Modulus of Elasticity	7.58 GPa	1100 ksi	
Flexural Strength	89.6 MPa	13000 psi	
Compressive Strength	203 MPa	29500 psi	

Thermal Properties	Metric	English	Comments
CTE, linear	16.9 $\mu\text{m/m}\cdot\text{Å}^\circ\text{C}$ @Temperature 20.0 $\text{Å}^\circ\text{C}$	9.40 $\mu\text{in/in}\cdot\text{Å}^\circ\text{F}$ @Temperature 68.0 $\text{Å}^\circ\text{F}$	
Thermal Conductivity	3.46 W/m-K	24.0 BTU-in/hr-ft $\text{Å}^2\cdot\text{Å}^\circ\text{F}$	
Maximum Service Temperature, Air	177 $\text{Å}^\circ\text{C}$	350 $\text{Å}^\circ\text{F}$	In oxygen
Maximum Service Temperature, Inert	204 $\text{Å}^\circ\text{C}$	399 $\text{Å}^\circ\text{F}$	Reducing Atm.

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China