

## SGL Carbon Group SIGRAFIL C® C25 M100 UNS Milled Carbon Fiber, Unsized Carbon Fiber

Category: Carbon, Carbon Fiber, Other Engineering Material, Composite Fibers

## **Material Notes:**

Milled SIGRAFIL C is excellent for making materials electrically conductive such as powders, dry mixtures, adhesives, floorings, aqueous adhesive systems and all aqueous mixing processes. Milled SIGRAFIL C fibers can be added to thermoplastic injection molding compounds and are also available in a pelletized form for improved handling characteristics. SIGRAFIL C fibers are optimized in terms of their mechanical properties to offer excellent physical handling and process feeding properties. SIGRAFIL C can be blended with a variety of resins. Information provided by SGL Carbon Group

## Order this product through the following link:

http://www.lookpolymers.com/polymer\_SGL-Carbon-Group-SIGRAFIL-C-C25-M100-UNS-Milled-Carbon-Fiber-Unsized-Carbon-Fiber.php

Physical Properties	Metric	English	Comments
Bulk Density	0.350 g/cc	0.0126 lb/in³	
Density	1.80 g/cc	0.0650 lb/in³	Fiber Density
Filament Diameter	7.5 µm	7.5 µm	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	3600 MPa	522000 psi	ASTM D3379-99
Elongation at Break	1.4 - 1.8 %	1.4 - 1.8 %	ASTM D3379-75
Modulus of Elasticity	225 GPa	32600 ksi	ASTM D3379-99

Electrical Properties	Metric	English	Comments
Volume Resistivity	0.0016 ohm-cm	0.0016 ohm-cm	

Descriptive Properties	Value	Comments
Carbon Content, wt %	>95	
Mean Fiber Length, mm	0.1	Milled

## Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers



Address: United North Road 215, Fengxian District, Shanghai City, China