

## SK Chemicals SKYTHANE® S392A Polyester Based Thermoplastic Polyurethane Elastomer

Category : Polymer , Thermoplastic , Elastomer, TPE , Polyurethane, TP , Thermoplastic Polyurethane, Elastomer, Polyester Grade

### Material Notes:

Description: SK Chemicals has supplied Thermoplastic Polyurethane Elastomer (TPU) under the name of SKYTHANE. Applications include: Keyboard Covers, Outsoles of Soccer Shoes, Wire and Cable, Airbags, Sheets and Film, Hoses and Tubing, Shoe Components, Fire Hoses. Information provided by SK Chemicals.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_SK-Chemicals-SKYTHANE-S392A-Polyester-Based-Thermoplastic-Polyurethane-Elastomer.php](http://www.lookpolymers.com/polymer_SK-Chemicals-SKYTHANE-S392A-Polyester-Based-Thermoplastic-Polyurethane-Elastomer.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.21 g/cc	1.21 g/cc	ASTM D792
Linear Mold Shrinkage	0.0040 cm/cm	0.0040 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	93	93	ASTM D2240
Hardness, Shore D	50	50	ASTM D2240
Tensile Strength, Ultimate	44.1 MPa	6400 psi	ASTM D412
Elongation at Break	650 %	650 %	ASTM D412
100% Modulus	0.0103 GPa	1.50 ksi	ASTM D412
300% Modulus	0.0200 GPa	2.90 ksi	ASTM D412
Resilience	37	37	Vertical Rebound; ASTM D2632
Tear Strength	118 kN/m	672 pli	Die C; ASTM D624
Taber Abrasion, mg/1000 Cycles	35	35	H18 wheel, 1000g load; ASTM D1044

Thermal Properties	Metric	English	Comments
Vicat Softening Point	110 Â°C	230 Â°F	ASTM D1525

Processing Properties	Metric	English	Comments
Processing Temperature	195 Â°C	383 Â°F	Transition Temperature
	195 Â°C	383 Â°F	Metering Temperature
Middle Barrel Temperature	190 Â°C	374 Â°F	

<b>Nozzle Temperature Processing Properties</b>	<b>200 Â°C Metric</b>	<b>392 Â°F English</b>	<b>Comments</b>
Zone 1	180 Â°C	356 Â°F	
Zone 2	185 Â°C	365 Â°F	
Zone 3	190 Â°C	374 Â°F	
Zone 4	195 Â°C	383 Â°F	
Adapter Temperature	195 Â°C	383 Â°F	
Die Temperature	195 Â°C	383 Â°F	Tip
	200 Â°C	392 Â°F	Body
Mold Temperature	20.0 - 40.0 Â°C	68.0 - 104 Â°F	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China