

## SSAB Tunplatt Docol® 350YP High-strength Steel

Category : Metal , Ferrous Metal , Alloy Steel , Low Alloy Steel

**Material Notes:**

High-strength Steel Comments: Docol YP - Cold Rolled Steel - HSLA. Property values are for cold-rolled steel; thicknesses 0.5 - 3.00 mm.

Iron content is approximate - exact composition is not reported by the manufacturer. Data provided by SSAB Tunplatt.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_SSAB-Tunplatt-Docol-350YP-High-strength-Steel.php](http://www.lookpolymers.com/polymer_SSAB-Tunplatt-Docol-350YP-High-strength-Steel.php)

Physical Properties	Metric	English	Comments
Density	7.87 g/cc	0.284 lb/in <sup>3</sup>	Estimated by MatWeb

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	410 - 510 MPa	59500 - 74000 psi	
Tensile Strength, Yield	350 - 440 MPa @Strain 0.200 %	50800 - 63800 psi @Strain 0.200 %	
Elongation at Break	>= 22 %	>= 22 %	A<sub>80</sub>
Bend Radius, Minimum	>= 0.00 t @Thickness 0.500 - 3.00 mm	>= 0.00 t @Thickness 0.0197 - 0.118 in	

Component Elements Properties	Metric	English	Comments
Iron, Fe	98 %	98 %	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China