

## SSAB Tunnplat Domex® 014 BOR Water quenched Boron Steel

Category: Metal, Ferrous Metal, Alloy Steel, Low Alloy Steel

## **Material Notes:**

Domex® is the brand name of hot rolled products from SSAB Tunnplat. Compared to conventional quenched and tempered steels, boron steel have several benefits including better formability. Boron steels are used for a wide variety of applications - as a wear material and as a high-strength structural steel. Examples include wear plate, screen plate, punching tools, spades, knives, saw blades, caterpillar tracks, and agricultural machinery. Data provided by SSAB Tunnplat.

## Order this product through the following link:

http://www.lookpolymers.com/polymer\_SSAB-Tunnplat-Domex-014-BOR-Water-quenched-Boron-Steel.php

Physical Properties	Metric	English	Comments
Density	7.87 g/cc	0.284 lb/in³	Estimated by MatWeb

Mechanical Properties	Metric	English	Comments
Hardness, Vickers	490	490	HV <sub>10</sub> ; approximate
Tensile Strength, Ultimate	1600 MPa	232000 psi	
Tensile Strength, Yield	1200 MPa	174000 psi	
Elongation at Break	10 %	10 %	A <sub>5</sub>
Impact	25	25	J/cm²; -20°C
	35	35	J/cm²; 20°C

Component Elements Properties	Metric	English	Comments
Boron, B	0.0030 %	0.0030 %	
Carbon, C	0.20 - 0.25 %	0.20 - 0.25 %	
Chromium, Cr	0.15 - 0.25 %	0.15 - 0.25 %	
Iron, Fe	98 %	98 %	As Remainder
Manganese, Mn	0.70 - 1.0 %	0.70 - 1.0 %	
Phosphorous, P	<= 0.030 %	<= 0.030 %	
Silicon, Si	0.20 - 0.35 %	0.20 - 0.35 %	
Sulfur, S	<= 0.025 %	<= 0.025 %	

## **Contact Songhan Plastic Technology Co.,Ltd.**



Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China