

**STAR Thermoplastic Alloys & Rubbers StarFlex<sup>®</sup> P 7355-9000 TPE**

Category : Polymer , Thermoplastic , Elastomer, TPE , Thermoplastic Elastomer, Melt-Processible Rubber

**Material Notes:**

**Product Description:** StarFlex P 7355-9000 is an easy processing TPE designed for injection molding **Features:** Soft Touch Rubbery Feel Good Weatherability FDA and medical grades available **Processing Method:** Injection Molding **Information Provided by STAR Thermoplastic Elastomers**

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_STAR-Thermoplastic-Alloys-Rubbers-StarFlex-P-7355-9000-TPE.php](http://www.lookpolymers.com/polymer_STAR-Thermoplastic-Alloys-Rubbers-StarFlex-P-7355-9000-TPE.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.14 g/cc	1.14 g/cc	ASTM D792
Viscosity	7000 cP	7000 cP	ASTM D3835
	@Shear Rate 10994 1/s, Temperature 210 Â°C	@Shear Rate 10994 1/s, Temperature 410 Â°F	

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	55	55	ASTM D2240
	@Time 10.0 sec	@Time 0.00278 hour	
Tensile Strength at Break	4.98 MPa	723 psi	Die C; ASTM D414
	@Time 7200 sec	@Time 2.00 hour	
Elongation at Break	955 %	955 %	Die C; ASTM D412
	@Time 7200 sec	@Time 2.00 hour	
300% Modulus	0.00181 GPa	0.263 ksi	Die C; ASTM D412
	@Time 7200 sec	@Time 2.00 hour	
Tear Strength	21.0 kN/m	120 pli	ASTM D624

Descriptive Properties	Value	Comments
Color	Black	

**Contact Songhan Plastic Technology Co.,Ltd.**

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China