

STAR Thermoplastic Alloys & Rubbers StarTUFF TF 35-HR-9 TPE

Category : Polymer , Thermoplastic , Elastomer, TPE , Thermoplastic Elastomer, Melt-Processible Rubber

Material Notes:

Product Description: StarTUFF TF 35-HR-9 is an easy processing TPE designed for injection molding **Features:**Soft TouchRubbery FeelHigh Tear strengthHigh Tensile strength**Processing Method:** Injection Molding**Information Provided by** STAR Thermoplastic Elastomers

Order this product through the following link:

http://www.lookpolymers.com/polymer_STAR-Thermoplastic-Alloys-Rubbers-StarTUFF-TF-35-HR-9-TPE.php

Physical Properties	Metric	English	Comments
Specific Gravity	0.920 g/cc	0.920 g/cc	ASTM D792
Viscosity	12000 cP	12000 cP	ASTM D3835
	@Shear Rate 10994 1/s, Temperature 210 Â°C	@Shear Rate 10994 1/s, Temperature 410 Â°F	

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	36	36	ASTM D2240
	@Time 10.0 sec	@Time 0.00278 hour	
Tensile Strength at Break	6.47 MPa	938 psi	Die C; ASTM D414
	@Time 7200 sec	@Time 2.00 hour	
Elongation at Break	725 %	725 %	Die C; ASTM D412
	@Time 7200 sec	@Time 2.00 hour	
300% Modulus	0.00154 GPa	0.224 ksi	Die C; ASTM D412
	@Time 7200 sec	@Time 2.00 hour	
Tear Strength	27.7 kN/m	158 pli	ASTM D624

Descriptive Properties	Value	Comments
Color	Black	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China