

SYNTHOS Kralex[®] 1721 Styrene Butadiene Rubber

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE)

Material Notes:

KRALEX[®] 1721 is a standard grade of oil extended styrene butadiene rubber. It is produced by a technology of cold emulsion polymerisation based on soaps of rosin and fatty acids and contains 40% of chemically bounded styrene. It is coagulated by a system of acid and organic coagulant, contains 27% (37 PHR) of extender oil (DAE grade) and is stabilized by a staining antioxidant. It is appropriate for rubber compounds used in the production of car tires and inner tubes, including tire re-trading, conveyor belts, footwear and various technical rubber articles. It is not approved for production of rubber articles coming into contact with foods or drinking water. Synthos was formerly known as Kaucuk. All information provided by Synthos.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SYNTHOS-Kralex-1721-Styrene-Butadiene-Rubber.php

Physical Properties	Metric	English	Comments
Volatiles	<= 0.75 %	<= 0.75 %	ASTM D5668
Mooney Viscosity	42 - 52	42 - 52	(15-1.5 min); ASTM D3346
	@Temperature 100 Â°C	@Temperature 212 Â°F	
	50 - 60	50 - 60	(1+4); ASTM D1646
	@Temperature 100 Â°C	@Temperature 212 Â°F	
Ash	<= 0.40 %	<= 0.40 %	ASTM D5667

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	18.5 MPa	2680 psi	35'/145Â°C; ASTM D412
Elongation at Break	370 %	370 %	35'/145Â°C; ASTM D412
300% Modulus	0.0120 - 0.0180 GPa	1.74 - 2.61 ksi	35'/145Â°C; ASTM D412

Chemical Properties	Metric	English	Comments
Acid Value	4.1 - 5.7	4.1 - 5.7	ASTM D5774
Styrene Content	40 %	40 %	ASTM D5775

Descriptive Properties	Value	Comments
50% of Vulcanization t' 50 (min.)	6-10	ASTM D5289
Antioxidant Grade	Staining	
Compound Safety ts 1 (min.)	2.7-5.3	ASTM D5289

Ethanol-toluene Extract (%) Descriptive Properties	29-35 Value	ASTM D5774 Comments
Extender Oil Content (%)	27	
Extender Oil Grade	DAE	
Maximal Moment (dNm)	14.5-18	ASTM D5289
Minimal Moment (dNm)	1.8-2.4	ASTM D5289
Optimal Vulcanization t' 90 (min.)	11-16	ASTM D5289
Soaps content (%)	<= 0.3	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China