

## SYNTHOS Kralex<sup>®</sup> 1723 Styrene Butadiene Rubber

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE)

### Material Notes:

KRALEX<sup>®</sup> 1723 is a Specific grade of oil extended styrene butadiene rubber. It is produced by a technology of cold emulsion polymerisation based on soaps of rosin and fatty acids and contains 23.5% of chemically bounded styrene. It is coagulated by a system of acid and organic coagulant, contains 27% (37 PHR) of extender oil with reduced content of polycyclic aromatics (TDAE grade) and is stabilized by a staining antioxidant. It is appropriate for rubber compounds used in the production of car tires and inner tubes, including tire re-trading, conveyor belts, shoes and various technical rubber articles. KRALEX<sup>®</sup> 1723 can be used in the same rubber compounds as KRALEX<sup>®</sup> 1712 if the presence of polycyclic aromatics is not desirable. It is not approved for production of rubber articles coming into contact with foods or drinking water. Synthos was formerly known as Kaucuk. All information provided by Synthos.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_SYNTHOS-Kralex-1723-Styrene-Butadiene-Rubber.php](http://www.lookpolymers.com/polymer_SYNTHOS-Kralex-1723-Styrene-Butadiene-Rubber.php)

Physical Properties	Metric	English	Comments
Volatiles	<= 0.75 %	<= 0.75 %	ASTM D5668
Mooney Viscosity	40 - 48	40 - 48	(15-1.5 min); ASTM D3346
	@Temperature 100 Â°C	@Temperature 212 Â°F	
	48 - 56	48 - 56	(1+4); ASTM D1646
	@Temperature 100 Â°C	@Temperature 212 Â°F	
Ash	<= 0.40 %	<= 0.40 %	ASTM D5667

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	18.5 MPa	2680 psi	35'/145Â°C; ASTM D412
Elongation at Break	370 %	370 %	35'/145Â°C; ASTM D412
300% Modulus	0.0120 - 0.0170 GPa	1.74 - 2.47 ksi	35'/145Â°C; ASTM D412

Chemical Properties	Metric	English	Comments
Acid Value	3.6 - 5.4	3.6 - 5.4	ASTM D5774
Styrene Content	23.5 %	23.5 %	ASTM D5775

Descriptive Properties	Value	Comments
50% of Vulcanization t' 50 (min.)	6-9	ASTM D5289
Antioxidant Grade	Staining	
Compound Safety ts 1 (min.)	2.5-4.5	ASTM D5289

Descriptive Properties	Value	Comments
Extender Oil Content (%)	27	
Extender Oil Grade	TDAE	
Maximal Moment (dNm)	15-18	ASTM D5289
Minimal Moment (dNm)	1.9-2.6	ASTM D5289
Optimal Vulcanization t' 90 (min.)	11-15	ASTM D5289
Soaps content (%)	<= 0.3	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China