

Saint-Gobain CHR® 2302-5R UHMW Film Backing Acrylic Adhesive Pressure Sensitive Tape

Category: Polymer, Adhesive, Tape, Thermoplastic, Acrylic (PMMA)

Material Notes:

Description: UHMW polyolefin film tape provides anti-sticking and abrasion resistance properties for application temperatures ranging from - $100\math{\^{A}}$ °F to $225\math{\^{A}}$ °F (- $73\math{\^{A}}$ °C to + $107\math{\^{A}}$ °C). Applications include bearings, chute and guide rail coverings. This tape uses an acrylic adhesive system. Acrylic adhesves perform in continuous operating temperatures from - $40\math{\^{A}}$ °F to + $375\math{\^{A}}$ °F (- $40\math{\^{A}}$ °C to + $188\math{\^{A}}$ °C). Benefits include exceptional solvent resistance, excellent adhesion to metal, superior weathering and aging characteristics. Acrylics have an excellent shelf life, and when exposed to elevated temperatures, their ability to wet-out improves thus increasing both adhesion and tack properties. All data based on a 0.0065 inch test sample. (Thickness given is for both backing and adhesive. Backing thickness is .005 inches.) Information provided by Saint Gobain Performance Products.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Saint-Gobain-CHR-2302-5R-UHMW-Film-Backing-Acrylic-Adhesive-Pressure-Sensitive-Tape.php

Mechanical Properties	Metric	English	Comments
Elongation at Break	350 %	350 %	
Tear Strength	7.01 kN/m	40.0 pli	Initial Tear Strength

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	107 °C	225 °F	
Minimum Service Temperature, Air	-40.0 °C	-40.0 °F	

Descriptive Properties	Value	Comments
Color	Natural	

Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China