

Saint-Gobain CHR[®] K290ESD Polyimide Film Backing Silicone Adhesive Pressure Sensitive Tape

Category : Polymer , Tape , Thermoset , Polyimide, TS , Silicone

Material Notes:

Description: Polyimide films are employed because of their extreme heat resistance. Service temperatures range from -100[°]F to 500[°]F (-73[°]C to 260[°]C). These flame retardant films exhibit high tensile strength and conformability, good solvent resistance, excellent dielectric strength and good abrasion resistance. Polyimide tape applications include electrical insulation, capacitor, transformer and coil wrapping, electronic assembly, and wave solder protection. This tape uses a silicone adhesive system. Perfect for extreme temperature applications, silicone adhesives perform in continuous operating temperatures from -100[°]F to 500[°]F (-73[°]C to 260[°]C). Silicone-based adhesive systems exhibit good chemical resistance, retain electrical properties, and remove cleanly with little or no residue. All data based on a 0.0027 inch test sample. (Thickness given is for both backing and adhesive. Backing thickness is .001 inches.) Information provided by Saint Gobain Performance Products.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Saint-Gobain-CHR-K290ESD-Polyimide-Film-Backing-Silicone-Adhesive-Pressure-Sensitive-Tape.php

Mechanical Properties	Metric	English	Comments
Elongation at Break	50 %	50 %	
Tear Strength	5.26 kN/m	30.0 pli	Initial Tear Strength

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	260 [°] C	500 [°] F	
Minimum Service Temperature, Air	-73.3 [°] C	-100 [°] F	

Electrical Properties	Metric	English	Comments
Dielectric Strength	118 kV/mm	3000 kV/in	
Dielectric Breakdown	7000 V	7000 V	

Descriptive Properties	Value	Comments
Color	Amber	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China