

Saint-Gobain COHRLastic[®] 400 General Purpose Silicone Solid Rubber

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE) , Silicone

Material Notes:

Description: COHRLastic[®] solid silicone rubber in square sheet and continuous length form has a smooth, blemish-free surface. It is available in degrees of hardness from relatively soft 30 durometer to the relatively hard 70 durometer on the Shore A scale. It is manufactured in different formulations to provide a choice of physical properties and cost considerations. Series 300-700: COHRLastic general-purpose molded sheet is available in thicknesses up to 1/2" and it withstands temperatures from -100[°]F to +500[°]F. RED in color. All data based on a 0.25 inch test sample. (Also comes in thicknesses from 1/16" to 1/2") Information provided by Saint Gobain Performance Products.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Saint-Gobain-COHRLastic-400-General-Purpose-Silicone-Solid-Rubber.php

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	35 - 45	35 - 45	Increases by 5 after dry heat aging for 70 hrs at 437 [°] F.; ASTM D2240
Tensile Strength, Yield	4.83 MPa	700 psi	Tensile strength decreases by 15% after dry heat aging for 70 hrs at 437 [°] F.; ASTM D412
Elongation at Break	400 %	400 %	Elongation properties decrease by 15% after dry heat aging for 70 hrs at 437 [°] F.; ASTM D412
Tear Strength	13.1 kN/m	75.0 pli	Initial Tear Strength; ASTM D624
Compression Set	15 % @Temperature 160 [°] C	15 % @Temperature 320 [°] F	Constant Deflection, 70 hrs.; ASTM D395

Thermal Properties	Metric	English	Comments
CTE, linear	270 [°] µm/m- [°] C @Temperature 20.0 [°] C	150 [°] µin/in- [°] F @Temperature 68.0 [°] F	
Specific Heat Capacity	1.26 J/g- [°] C	0.300 BTU/lb- [°] F	
Thermal Conductivity	0.187 W/m-K	1.30 BTU-in/hr-ft ² - [°] F	

Electrical Properties	Metric	English	Comments
Dielectric Strength	19.7 kV/mm	500 kV/in	

Descriptive Properties	Value	Comments
Color	Red	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China