

## Saint-Gobain COHRlastic® 500 General Purpose Silicone Solid Rubber

Category: Polymer, Thermoset, Rubber or Thermoset Elastomer (TSE), Silicone

## **Material Notes:**

Description: COHRlastic® solid silicone rubber in square sheet and continuous length form has a smooth, blemish-free surface. It is available in degrees of hardness from relatively soft 30 durometer to the relatively hard 70 durometer on the Shore A scale. It is manufactured in different formulations to provide a choice of physical properties and cost considerations. Series 300-700: COHRlastic general-purpose molded sheet is available in thicknesses up to 1/2" and it withstands temperatures from -100°F to +500°F. RED in color.All data based on a 0.25 inch test sample.(Also comes in thicknesses from 1/16" to 1/2") Information provided by Saint Gobain Performance Products.

## Order this product through the following link:

http://www.lookpolymers.com/polymer\_Saint-Gobain-COHRlastic-500-General-Purpose-Silicone-Solid-Rubber.php

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	45 - 55	45 - 55	Increases by 5 after dry heat aging for 70 hrs at 437°F.; ASTM D2240
Tensile Strength, Yield	4.83 MPa	700 psi	Tensile strength decreases by 15% after dry heat aging for 70 hrs at 437°F.; ASTM D412
Elongation at Break	350 %	350 %	Elongation properties decrease by 15% after dry heat aging for 70 hrs at 437°F.; ASTM D412
Tear Strength	12.3 kN/m	70.0 pli	Initial Tear Strength; ASTM D624
Compression Set	15 %	15 %	Constant Deflection, 70 hrs.; ASTM D395
	@Temperature 160 °C	@Temperature 320 °F	

Thermal Properties	Metric	English	Comments
CTE, linear	270 Âμm/m-°C	150 Âμin/in-°F	
	@Temperature 20.0 °C	@Temperature 68.0 °F	
Specific Heat Capacity	1.26 J/g-°C	0.300 BTU/lb-°F	
Thermal Conductivity	0.187 W/m-K	1.30 BTU-in/hr-ft²- °F	

Electrical Properties	Metric	English	Comments
Dielectric Strength	19.7 kV/mm	500 kV/in	

Descriptive Properties	Value	Comments
Color	Red	



## **Contact Songhan Plastic Technology Co.,Ltd.**

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China