Saint-Gobain COHRlastic® 600 General Purpose Silicone Solid Rubber

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE) , Silicone

Material Notes:

Color

Description: COHRlastic® solid silicone rubber in square sheet and continuous length form has a smooth, blemish-free surface. It is available in degrees of hardness from relatively soft 30 durometer to the relatively hard 70 durometer on the Shore A scale. It is manufactured in different formulations to provide a choice of physical properties and cost considerations. Series 300-700: COHRlastic general-purpose molded sheet is available in thicknesses up to 1/2" and it withstands temperatures from -100°F to +500°F. RED in color.All data based on a 0.25 inch test sample.(Also comes in thicknesses from 1/16" to 1/2") Information provided by Saint Gobain Performance Products.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Saint-Gobain-COHRlastic-600-General-Purpose-Silicone-Solid-Rubber.php

Mechanical Properties	Metric	English	Comments	
Hardness, Shore A	55 - 65	55 - 65	Increases by 5 after dry heat aging for 70 hrs at 437°F.; ASTM D2240	
Tensile Strength, Yield	4.83 MPa	700 psi	Tensile strength decreases by 15% after dry heat aging for 70 hrs at 437°F.; ASTM D412	
Elongation at Break	200 %	200 %	Elongation properties decrease by 15% after dry heat aging for 70 hrs at 437°F.; ASTM D412	
Tear Strength	11.4 kN/m	65.0 pli	Initial Tear Strength; ASTM D624	
Compression Set	15 %	15 %	Constant Deflection, 70 hrs.; ASTM D395	
	@Temperature 160 °C	@Temperature 320 °F		

Thermal Properties	Metric	English	Comments	
	270 µm/m-°C	150 µin/in-°F		
CTE, linear	@Temperature 20.0 °C	@Temperature 68.0 °F		
Specific Heat Capacity	1.26 J/g-°C	0.300 BTU/lb-°F		
Thermal Conductivity	0.187 W/m-K	1.30 BTU-in/hr-ft²- °F		

Electrical Properties	Metric	English	Comments	
Dielectric Strength	19.7 kV/mm	500 kV/in		
Descriptive Properties		Value	Comments	

Red



Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com Email : sales@lookpolymers.com Tel : +86 021-51131842 Mobile : +86 13061808058 Skype : lookpolymers Address : United North Road 215,Fengxian District, Shanghai City,China