

## Saint-Gobain COHRLastic® 700 General Purpose Silicone Solid Rubber

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE) , Silicone

### Material Notes:

Description: COHRLastic® solid silicone rubber in square sheet and continuous length form has a smooth, blemish-free surface. It is available in degrees of hardness from relatively soft 30 durometer to the relatively hard 70 durometer on the Shore A scale. It is manufactured in different formulations to provide a choice of physical properties and cost considerations. Series 300-700: COHRLastic general-purpose molded sheet is available in thicknesses up to 1/2" and it withstands temperatures from -100°F to +500°F. RED in color. All data based on a 0.25 inch test sample. (Also comes in thicknesses from 1/16" to 1/2") Information provided by Saint Gobain Performance Products.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Saint-Gobain-COHRLastic-700-General-Purpose-Silicone-Solid-Rubber.php](http://www.lookpolymers.com/polymer_Saint-Gobain-COHRLastic-700-General-Purpose-Silicone-Solid-Rubber.php)

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	65 - 75	65 - 75	Increases by 5 after dry heat aging for 70 hrs at 437°F.; ASTM D2240
Tensile Strength, Yield	4.83 MPa	700 psi	Tensile strength decreases by 15% after dry heat aging for 70 hrs at 437°F.; ASTM D412
Elongation at Break	160 %	160 %	Elongation properties decrease by 15% after dry heat aging for 70 hrs at 437°F.; ASTM D412
Tear Strength	10.5 kN/m	60.0 pli	Initial Tear Strength; ASTM D624
Compression Set	15 % @Temperature 160 °C	15 % @Temperature 320 °F	Constant Deflection, 70 hrs.; ASTM D395

Thermal Properties	Metric	English	Comments
CTE, linear	270 Åµm/m-Å°C @Temperature 20.0 Å°C	150 Åµin/in-Å°F @Temperature 68.0 Å°F	
Specific Heat Capacity	1.26 J/g-Å°C	0.300 BTU/lb-Å°F	
Thermal Conductivity	0.187 W/m-K	1.30 BTU-in/hr-ftÅ²-Å°F	

Electrical Properties	Metric	English	Comments
Dielectric Strength	19.7 kV/mm	500 kV/in	

Descriptive Properties	Value	Comments
Color	Red	

## **Contact Songhan Plastic Technology Co.,Ltd.**

**Website : [www.lookpolymers.com](http://www.lookpolymers.com)**

**Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)**

**Tel : +86 021-51131842**

**Mobile : +86 13061808058**

**Skype : lookpolymers**

**Address : United North Road 215,Fengxian District, Shanghai City,China**