

## Saint-Gobain COHRLastic® 9060 Wide Series General Purpose Silicone Solid Rubber

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE) , Silicone

### Material Notes:

Description: COHRLastic® solid silicone rubber in square sheet and continuous length form has a smooth, blemish-free surface. It is available in degrees of hardness from relatively soft 30 durometer to the relatively hard 70 durometer on the Shore A scale. It is manufactured in different formulations to provide a choice of physical properties and cost considerations. Series 9030-9070: COHRLastic 9030 - 9070 series is also general purpose (similar to 300 - 700 series), but is produced in 36" wide continuous lengths for the most efficient utilization of material, minimizing waste. Standard thicknesses are 1/32", 1/16" and 1/8". Withstands temperatures from -100°F to 500°F. RED in color. All data based on a 0.0625 inch test sample. (Also comes in thicknesses from 1/32" to 1/8") Information provided by Saint Gobain Performance Products.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Saint-Gobain-COHRLastic-9060-Wide-Series-General-Purpose-Silicone-Solid-Rubber.php](http://www.lookpolymers.com/polymer_Saint-Gobain-COHRLastic-9060-Wide-Series-General-Purpose-Silicone-Solid-Rubber.php)

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	55 - 65	55 - 65	Increases by 5 after dry heat aging for 70 hrs at 437°F.; ASTM D2240
Tensile Strength, Yield	4.83 MPa	700 psi	Tensile strength decreases by 10% after dry heat aging for 70 hrs at 437°F.; ASTM D412
Elongation at Break	200 %	200 %	Elongation properties decrease by 20% after dry heat aging for 70 hrs at 437°F.; ASTM D412
Tear Strength	8.77 kN/m	50.0 pli	Initial Tear Strength; ASTM D624
Compression Set	20 % @Temperature 160 °C	20 % @Temperature 320 °F	Constant Deflection, 70 hrs.; ASTM D395

Thermal Properties	Metric	English	Comments
CTE, linear	270 µm/m-°C @Temperature 20.0 °C	150 µin/in-°F @Temperature 68.0 °F	
Specific Heat Capacity	1.26 J/g-°C	0.300 BTU/lb-°F	
Thermal Conductivity	0.187 W/m-K	1.30 BTU-in/hr-ft²-°F	

Electrical Properties	Metric	English	Comments
Dielectric Strength	19.7 kV/mm	500 kV/in	

Descriptive Properties	Value	Comments
Color	Red	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China