

## Saint-Gobain COHRLastic® CF4480 High Heat Reversion Resistant Reinforced Solid Rubber

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE)

### Material Notes:

Description: COHRLastic® CF silicone solid rubber reinforced with fiberglass is a dimensionally-stable, durable material for press pads, belting and gasketing. It is available in six constructions. CF 4480 utilizes the most reversion-resistant silicone rubber compound. The product is designed for use in applications involving the tough combination of prolonged high-pressure confinement at temperatures in the range of 375°F to 650°F. All data based on a 0.0625 inch test sample. (Tolerance of .005"; Thickness shown is for silicone rubber. Fiberglass thickness = 0.014".) Information provided by Saint Gobain Performance Products.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Saint-Gobain-COHRLastic-CF4480-High-Heat-Reversion-Resistant-Reinforced-Solid-Rubber.php](http://www.lookpolymers.com/polymer_Saint-Gobain-COHRLastic-CF4480-High-Heat-Reversion-Resistant-Reinforced-Solid-Rubber.php)

Physical Properties	Metric	English	Comments
Volatile Organic Compounds (VOC) Content	<= 0.50 g/l	<= 0.50 g/l	Weight Loss (4 hrs at 400°F)

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	81	81	
Elongation at Break	<= 10 %	<= 10 %	
Flexural Strength	5.17 MPa	750 psi	Diaphragm Burst Strength
Tear Strength	52.6 kN/m	300 pli	

Thermal Properties	Metric	English	Comments
CTE, linear	270 $\mu\text{m/m-}^\circ\text{C}$ @Temperature 20.0 $^\circ\text{C}$	150 $\mu\text{in/in-}^\circ\text{F}$ @Temperature 68.0 $^\circ\text{F}$	Silicone rubber component
Thermal Conductivity	0.274 W/m-K	1.90 BTU-in/hr-ft $^2$ - $^\circ\text{F}$	

Electrical Properties	Metric	English	Comments
Dielectric Strength	19.7 kV/mm	500 kV/in	

Descriptive Properties	Value	Comments
Color	Dark Gray	

Contact Songhan Plastic Technology Co.,Ltd.

**Website : [www.lookpolymers.com](http://www.lookpolymers.com)**

**Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)**

**Tel : +86 021-51131842**

**Mobile : +86 13061808058**

**Skype : lookpolymers**

**Address : United North Road 215,Fengxian District, Shanghai City,China**