

Saint-Gobain Chemfab® 313XK PTFE Coated Fiberglass/Kevlar Conveyor Belting

Category : Ceramic , Glass , Glass Fiber

Material Notes:

Description: General Notes on Saint Gobain Belting Products: Saint Gobain Performance Plastics developed its belting materials for applications that require superior release characteristics, permeability for rapid drying, dimensional and thermal stability, and the dynamic strength to stand up to the most rigorous operating conditions. The unique behavior of the materials results in a product that is more practical and cost-effective than conventional belting materials. **Release Properties:** The release characteristics of PTFE are superior to those of any other high-temperature material. This non-stick property is retained over a full range of operating temperatures. **Permeability:** Our belting combines a maximum amount of open area with good mechanical strength. The result is a very high level of controlled air flow through the belt, maximizing the rate of drying. **Dimensional Stability:** The woven reinforcement results in an elongation of approximately 1% under normal mechanical loading, even at temperatures of 550°F. Length distortion is exceptionally low, while width rigidity and stability are enhanced by the high modulus of the reinforcement. **Thermal Stability:** Chemfab® brand belting may be used continuously at temperatures up to 550°F without reducing its performance. **Dynamic Stability:** Our belting has been subjected to static and dynamic tests which indicate that it can withstand all normal operating conditions affecting service life. **Chemical Resistance:** PTFE surfaces are unaffected by most chemicals and solvents. **Notes on 313XK PTFE Coated Fiberglass/Kevlar Conveyor Belting:** Chemfab® 313XK is a belting product used in applications that require high strength and low elongation. This material has inherent stability that enhances its ability to resist ridging, puckering and creasing. The surface is textured because of the use of large yarns in the fiberglass substrate. The addition of Kevlar® in the warp gives added strength in terms of both tensile and tears, and also provides excellent flex fatigue resistance and moisture resistance. The substrate is fiberglass/Kevlar and the coating material is PTFE (PTFE = polytetrafluoroethylene). All data based on a 0.03 inch test sample. Information provided by Saint Gobain Performance Products.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Saint-Gobain-Chemfab-313XK-PTFE-Coated-FiberglassKevlar-Conveyor-Belting.php

Physical Properties	Metric	English	Comments
Density	1.557 g/cc	0.05626 lb/in ³	

Mechanical Properties	Metric	English	Comments
Elongation at Yield	<= 1.0 %	<= 1.0 %	Value given for Elongation at a loading of 40 lbs/in
Tear Strength Test	45	45	Lbs./In. Propagation Tear Strength in fill/transverse direction
	130	130	Lbs./In. for warp/longitudinal Propagation Tear Strength
Tear Strength	96.4 kN/m	550 pli	Tensile Strength (Fill)
	158 kN/m	900 pli	Tensile Strength (Warp)

Descriptive Properties	Value	Comments
------------------------	-------	----------

Weight (oz/vd ³) Descriptive Properties	35 Value	Comments
--	-------------	----------

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China