

Saint-Gobain Korel[®] K30-15 Soft Micro-cellular Polyurethane Foam

Category : Polymer , Thermoset , Polyurethane, TS , Thermoset Polyurethane Foam, Unreinforced

Material Notes:

Description: The Korel[®] series micro-cellular polyurethane foams are offered in a broad range of properties, making them ideal for a variety of gasketing and energy absorption needs. Korel[®] microcellular foams are categorized by degree of deflection force. By varying the modulus and density, Saint Gobain Performance Plastics has developed this series of materials that meets the demands of design engineers today. All Korel fians are available with an aggressive acrylic adhesive on one side to facilitate placement. Korel K30 foams are soft, conformable, low deflection, urethane foams offering excellent compression set resistance and low out-gassing that exceeds fogging requirements. K30 is ideal for open/close applications.**FEATURES/BENEFITS:**Excellent compression set resistanceHighly resilient (will not collapse)Dissipates stressesResistant to moisture and most chemicalsConformable and flexible even in extreme environmental conditionsEasy to achieve intricate die-cut partsAggressive acrylic adhesive (optional) facilitates assemblyAvailable cast on to polyester film for stability and low deformation**Typical Applications:** Cellular telephones, electrical enclosures, electronic gasketing, vibration damping, cushioning, acoustical control, bumpers, instrument panels, spacers.**Specification Notes:** Passes Fogging Test SAE-J 1756, 3 hrs. at 212[°]F (100[°]C). All data based on a 0.25 inch test sample.(Available in multiple thicknesses.) Information provided by Saint Gobain Performance Products.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Saint-Gobain-Korel-K30-15-Soft-Micro-cellular-Polyurethane-Foam.php

Physical Properties	Metric	English	Comments
Density	0.241 g/cc	0.00870 lb/in ³	ASTM D1667
Water Absorption	15 %	15 %	% by weight; ASTM D3574

Mechanical Properties	Metric	English	Comments
Hardness, Shore O	28	28	ASTM D2240
Tensile Strength, Yield	0.841 MPa	122 psi	ASTM D3574
Elongation at Break	485 %	485 %	ASTM D3574
Tensile Modulus	0.000345 GPa	0.0500 ksi	ASTM D3574
Compressive Strength	0.0345 MPa	5.00 psi	Compression Deflection, Value given for 12.7 mm/min, 25% deflection.; ASTM D3574 Test C
Compressive Modulus	0.0000621 GPa	0.00900 ksi	Force to Compress, Value given for 25% compression; ASTM D1667
Tear Strength	3.33 kN/m	19.0 pli	Initial Tear Strength; ASTM D624 Die C
Compression Set	<= 2.0 %	<= 2.0 %	Constant Deflection at 73 [°] F; ASTM D 3574 Test D
	<= 7.0 %	<= 7.0 %	Constant Deflection; ASTM D 3574

Mechanical Properties	Metric	English	Test D Comments
-----------------------	--------	---------	--------------------

Thermal Properties	Metric	English	Comments
Thermal Conductivity	0.0865 W/m-K	0.600 BTU-in/hr-ft ² - Â°F	ASTM E1530
Maximum Service Temperature, Air	70.0 Â°C	158 Â°F	Constant use
	121 Â°C	250 Â°F	Intermittent

Electrical Properties	Metric	English	Comments
Volume Resistivity	2.00e+12 ohm-cm	2.00e+12 ohm-cm	
Surface Resistivity per Square	9.10e+13 ohm	9.10e+13 ohm	
Dielectric Strength	1.89 kV/mm	48.0 kV/in	ASTM D149

Descriptive Properties	Value	Comments
Standard Color	Black	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China