

Saint-Gobain Korel[®] K40-30 Medium Deflection Micro-cellular Polyurethane Foam

Category : Polymer , Thermoset , Polyurethane, TS , Thermoset Polyurethane Foam, Unreinforced

Material Notes:

Description: The Korel[®] series micro-cellular polyurethane foams are offered in a broad range of properties, making them ideal for a variety of gasketing and energy absorption needs. Korel[®] microcellular foams are categorized by degree of deflection force. By varying the modulus and density, Saint Gobain Performance Plastics has developed this series of materials that meets the demands of design engineers today. All Korel foams are available with an aggressive acrylic adhesive on one side to facilitate placement. Korel K40 series is a medium deflection urethane foam with minimal compression set. As with the K30, this series also offers low out-gassing and exceeds fogging requirements.
FEATURES/BENEFITS: Excellent compression set resistance Highly resilient (will not collapse) Dissipates stresses Resistant to moisture and most chemicals Conformable and flexible even in extreme environmental conditions Easy to achieve intricate die-cut parts Aggressive acrylic adhesive (optional) facilitates assembly Available cast on to polyester film for stability and low deformation
Typical Applications: Cellular telephones, electrical enclosures, electronic gasketing, vibration damping, cushioning, acoustical control, bumpers, instrument panels, spacers.
Specification Notes: UL Testing (JMST2) UL 50 and UL 508 File MH26338; Passes Fogging Test SAE-J 1756, 3 hrs. at 212[°]F (100[°]C). All data based on a 0.02 inch test sample. (Available in multiple thicknesses.) Information provided by Saint Gobain Performance Products.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Saint-Gobain-Korel-K40-30-Medium-Deflection-Micro-cellular-Polyurethane-Foam.php

Physical Properties	Metric	English	Comments
Density	0.471 g/cc	0.0170 lb/in ³	ASTM D1667
Water Absorption	10 %	10 %	% by weight; ASTM D3574

Mechanical Properties	Metric	English	Comments
Hardness, Shore O	53	53	ASTM D2240
Tensile Strength, Yield	0.414 MPa	60.0 psi	ASTM D3574
Elongation at Break	250 %	250 %	ASTM D3574
Tensile Modulus	0.000345 GPa	0.0500 ksi	ASTM D3574
Compressive Strength	0.0621 MPa	9.00 psi	Compression Deflection, Value given for 12.7 mm/min, 25% deflection.; ASTM D3574 Test C
Compressive Modulus	0.0000896 GPa	0.0130 ksi	Force to Compress, Value given for 25% compression; ASTM D1667
Tear Strength	3.51 kN/m	20.0 pli	Initial Tear Strength; ASTM D624 Die C
Compression Set	<= 2.0 %	<= 2.0 %	Constant Deflection at 73 [°] F; ASTM D 3574 Test D

Mechanical Properties	Metric	English	Comments
	$\leq 7.0\%$ @Temperature 70.0 Â°C	$\leq 7.0\%$ @Temperature 158 Â°F	Compression Deflection; ASTM D 3574 Test D

Thermal Properties	Metric	English	Comments
Thermal Conductivity	0.0865 W/m-K	0.600 BTU-in/hr-Â²- Â°F	ASTM E1530
Maximum Service Temperature, Air	70.0 Â°C	158 Â°F	Constant use
	121 Â°C	250 Â°F	Intermittent

Electrical Properties	Metric	English	Comments
Volume Resistivity	3.20e+14 ohm-cm	3.20e+14 ohm-cm	
Surface Resistivity per Square	1.50e+13 ohm	1.50e+13 ohm	
Dielectric Strength	1.85 kV/mm	47.0 kV/in	ASTM D149

Descriptive Properties	Value	Comments
Standard Color	Black	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China