

Saint-Gobain Norton® Chemfilm® MR Fluoropolymer Cast Film

Category : Polymer , Film , Thermoplastic , Fluoropolymer

Material Notes:

Description: Commonly used for Aerospace/Release Film Applications Information provided by Saint Gobain Performance Products.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Saint-Gobain-Norton-Chemfilm-MR-Fluoropolymer-Cast-Film.php

Physical Properties	Metric	English	Comments
Specific Gravity	2.15 g/cc	2.15 g/cc	ASTM D-792
Water Absorption	<= 0.010 %	<= 0.010 %	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	31.0 MPa	4500 psi	ASTM D-882
Elongation at Break	400 %	400 %	ASTM D-882
Tensile Modulus	0.379 GPa	55.0 ksi	ASTM D-882
Tear Strength	193 kN/m	1100 pli	Initial Tear Strength; ASTM D-1004

Thermal Properties	Metric	English	Comments
CTE, linear	99.0 $\mu\text{m}/\text{m}\cdot\text{Å}^\circ\text{C}$ @Temperature 20.0 $\text{Å}^\circ\text{C}$	55.0 $\mu\text{in}/\text{in}\cdot\text{Å}^\circ\text{F}$ @Temperature 68.0 $\text{Å}^\circ\text{F}$	ASTM D-696
Melting Point	327 $\text{Å}^\circ\text{C}$	620 $\text{Å}^\circ\text{F}$	ASTM D-3418
Maximum Service Temperature, Air	260 $\text{Å}^\circ\text{C}$	500 $\text{Å}^\circ\text{F}$	UL-746 B
Flammability, UL94	V-0	V-0	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China