

## Saint-Gobain Norton® Fluorglas® Chemfilm® DF1471 Conductive PTFE Tape

Category : Polymer , Film , Thermoplastic , Fluoropolymer , PTFE , Polytetrafluoroethylene (PTFE), Molded

### Material Notes:

Description: Chemfilm® Fluoropolymer Cast Films and Tapes for Wire and Cable Industry: Multi-layer cast film process ensures inherently pin-hole free structure, therefore cast films possess superior dielectric properties. The multi-layer process is ideal for bulk and surface properties suited to most demanding applications. DF1400 Series--Low noise cable applications: The DF1400 has a non-conductive, fully fused, PTFE core coated with a conductive fluoropolymer formulation designed to be applied over jacketed wire and cable using standard tape-wrap equipment. It may be bondable with FEP or PFA. The DF1471 is a fully conductive PTFE that is also available with a conductive FEP surface. PTFE = polytetrafluoroethylene Applications include: Wire and Cable Industry Applications Information provided by Saint Gobain Performance Products.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Saint-Gobain-Norton-Fluorglas-Chemfilm-DF1471-Conductive-PTFE-Tape.php](http://www.lookpolymers.com/polymer_Saint-Gobain-Norton-Fluorglas-Chemfilm-DF1471-Conductive-PTFE-Tape.php)

Physical Properties	Metric	English	Comments
Specific Gravity	2.15 g/cc	2.15 g/cc	ASTM D-792
Water Absorption	<= 0.010 %	<= 0.010 %	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	27.6 MPa	4000 psi	ASTM D-882
Elongation at Break	400 %	400 %	ASTM D-882
Tensile Modulus	0.414 GPa	60.0 ksi	ASTM D-882

Thermal Properties	Metric	English	Comments
Melting Point	327 Å°C	620 Å°F	ASTM D-3418
Maximum Service Temperature, Air	260 Å°C	500 Å°F	UL-746 B
Minimum Service Temperature, Air	-240 Å°C	-400 Å°F	
Flammability, UL94	V-0	V-0	

Electrical Properties	Metric	English	Comments
Dielectric Constant	12	12	ASTM D-150
	@Frequency 60.0 - 1.00e+8 Hz	@Frequency 60.0 - 1.00e+8 Hz	
Dissipation Factor	0.036	0.036	ASTM D-150

## **Contact Songhan Plastic Technology Co.,Ltd.**

**Website : [www.lookpolymers.com](http://www.lookpolymers.com)**

**Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)**

**Tel : +86 021-51131842**

**Mobile : +86 13061808058**

**Skype : lookpolymers**

**Address : United North Road 215,Fengxian District, Shanghai City,China**