

Samsung Cheil Industries Infino[®] HN-1064 PC, Unreinforced FR

Category : Polymer , Thermoplastic , Polycarbonate (PC) , Polycarbonate, Molded

Material Notes:

PC material that is applied to other resin for mobile phone chargers Information provided by Samsung Cheil Industries.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Samsung-Cheil-Industries-Infino-HN-1064-PC-Unreinforced-FR.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.20 g/cc	1.20 g/cc	ASTM D792
Linear Mold Shrinkage, Flow	0.0050 - 0.0070 cm/cm @Thickness 3.20 mm	0.0050 - 0.0070 in/in @Thickness 0.126 in	ASTM D955
Melt Flow	38 g/10 min @Load 10.0 kg, Temperature 250 Å°C	38 g/10 min @Load 22.0 lb, Temperature 482 Å°F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	57.9 MPa	8390 psi	5 mm/min; ASTM D638
Flexural Strength	82.4 MPa	12000 psi	2.8 mm/min; ASTM D790
Flexural Modulus	2.06 GPa	299 ksi	2.8 mm/min; ASTM D790
Izod Impact, Notched	5.88 J/cm @Thickness 3.17 mm	11.0 ft-lb/in @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	130 Å°C @Thickness 6.40 mm	266 Å°F @Thickness 0.252 in	ASTM D648
Vicat Softening Point	140 Å°C	284 Å°F	B/50; ISO R306
UL RTI, Electrical	130 Å°C	266 Å°F	
UL RTI, Mechanical with Impact	130 Å°C	266 Å°F	
UL RTI, Mechanical without Impact	130 Å°C	266 Å°F	
Flammability, UL94	V-2 @Thickness 0.750 mm	V-2 @Thickness 0.0295 in	
	V-0 @Thickness 1.50 - 3.00	V-0 @Thickness 0.0591 -	

Thermal Properties	mm Metric	0.118 in English	Comments
--------------------	--------------	---------------------	----------

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China