

Samsung Cheil Industries Infino[®] LB-1010W PC, Unreinforced FR

Category : Polymer , Thermoplastic , Polycarbonate (PC) , Polycarbonate, Molded

Material Notes:

Information provided by Samsung Cheil Industries.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Samsung-Cheil-Industries-Infino-LB-1010W-PC-Unreinforced-FR.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.26 g/cc	1.26 g/cc	ASTM D792
Linear Mold Shrinkage, Flow	0.0050 - 0.0070 cm/cm @Thickness 3.20 mm	0.0050 - 0.0070 in/in @Thickness 0.126 in	ASTM D955
Melt Flow	50 g/10 min @Load 10.0 kg, Temperature 250 Å°C	50 g/10 min @Load 22.0 lb, Temperature 482 Å°F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	120	120	ASTM D785
Tensile Strength, Yield	52.0 MPa	7540 psi	50 mm/min; ASTM D638
Flexural Strength	76.5 MPa	11100 psi	2.8 mm/min; ASTM D790
Flexural Modulus	2.06 GPa	299 ksi	2.8 mm/min; ASTM D790
Izod Impact, Notched	4.90 J/cm @Thickness 3.17 mm	9.18 ft-lb/in @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	129 Å°C @Thickness 6.40 mm	264 Å°F @Thickness 0.252 in	ASTM D648
Vicat Softening Point	139 Å°C	282 Å°F	B/50; ISO R306
Flammability, UL94	V-2 @Thickness 0.750 mm	V-2 @Thickness 0.0295 in	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China