

Samsung Cheil Industries Starex[®] CR-0760 ABS, Unreinforced

Category : Polymer , Thermoplastic , ABS Polymer , Acrylonitrile Butadiene Styrene (ABS), Molded

Material Notes:

Good chemical resistance Information provided by Samsung Cheil Industries.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Samsung-Cheil-Industries-Starex-CR-0760-ABS-Unreinforced.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.04 g/cc	1.04 g/cc	ASTM D792
Melt Flow	3.7 g/10 min @Load 5.00 kg, Temperature 200 °C	3.7 g/10 min @Load 11.0 lb, Temperature 392 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	106	106	ASTM D785
Tensile Strength, Yield	41.2 MPa	5970 psi	5 mm/min; ASTM D638
Flexural Strength	57.9 MPa	8400 psi	2.8 mm/min; ASTM D790
Flexural Modulus	1.96 GPa	284 ksi	2.8 mm/min; ASTM D790
Izod Impact, Notched	1.77 J/cm @Thickness 6.35 mm	3.31 ft-lb/in @Thickness 0.250 in	ASTM D256

Thermal Properties	Metric	English	Comments
Vicat Softening Point	95.0 °C	203 °F	B/50; ISO R306

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China