

Samsung Cheil Industries Starex[®] SP-0183 ABS, Unreinforced Extrusion Grade

Category : Polymer , Thermoplastic , ABS Polymer , Acrylonitrile Butadiene Styrene (ABS), Extruded

Material Notes:

Information provided by Samsung Cheil Industries.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Samsung-Cheil-Industries-Starex-SP-0183-ABS-Unreinforced-Extrusion-Grade.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.04 g/cc	1.04 g/cc	ASTM D792
Melt Flow	3.5 g/10 min @Load 10.0 kg, Temperature 220 Å°C	3.5 g/10 min @Load 22.0 lb, Temperature 428 Å°F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	100	100	ASTM D785
Tensile Strength, Yield	41.2 MPa	5970 psi	5 mm/min; ASTM D638
Elongation at Break	50 %	50 %	5 mm/min; ASTM D638
Flexural Strength	60.8 MPa	8820 psi	2.8 mm/min; ASTM D790
Flexural Modulus	1.86 GPa	270 ksi	2.8 mm/min; ASTM D790
Izod Impact, Notched	4.02 J/cm @Thickness 6.35 mm	7.53 ft-lb/in @Thickness 0.250 in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	91.0 Å°C @Thickness 6.40 mm	196 Å°F @Thickness 0.252 in	ASTM D648
Vicat Softening Point	101 Å°C	214 Å°F	B/50; ISO R306

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China