

## Samsung Cheil Industries Starex<sup>®</sup> SR-0310 Heat Resistant Grade ABS

Category : Polymer , Thermoplastic , ABS Polymer , Acrylonitrile Butadiene Styrene (ABS), Heat Resistant, Molded

### Material Notes:

Information provided by Polymer Technology and Services, LLC (PTS).

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Samsung-Cheil-Industries-Starex-SR-0310-Heat-Resistant-Grade-ABS.php](http://www.lookpolymers.com/polymer_Samsung-Cheil-Industries-Starex-SR-0310-Heat-Resistant-Grade-ABS.php)

Physical Properties	Metric	English	Comments
Density	1.04 g/cc	0.0376 lb/in <sup>3</sup>	ASTM D792
Melt Flow	13 g/10 min @Load 10.0 kg, Temperature 220 °C	13 g/10 min @Load 22.0 lb, Temperature 428 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	108	108	ASTM D785
Tensile Strength, Yield	49.0 MPa @Thickness 3.17 mm	7100 psi @Thickness 0.125 in	ASTM D638
Flexural Strength	70.3 MPa @Thickness 3.17 mm	10200 psi @Thickness 0.125 in	ASTM D790
Flexural Modulus	2.28 GPa @Thickness 3.17 mm	330 ksi @Thickness 0.125 in	ASTM D790
Izod Impact, Notched	2.46 J/cm @Thickness 3.17 mm	4.60 ft-lb/in @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	92.8 °C @Thickness 6.35 mm	199 °F @Thickness 0.250 in	Unannealed; ASTM D648
Vicat Softening Point	105 °C	221 °F	Unannealed; ISO R-306
Flammability, UL94	HB @Thickness 1.50 mm	HB @Thickness 0.0591 in	
	HB @Thickness 6.00 mm	HB @Thickness 0.236 in	
	HB	HB	

Thermal Properties	@Thickness 3.00 mm Metric	@Thickness 0.118 in English	Comments
<b>Processing Properties</b>	<b>Metric</b>	<b>English</b>	<b>Comments</b>
Rear Barrel Temperature	190 - 210 Â°C	374 - 410 Â°F	
Middle Barrel Temperature	220 - 240 Â°C	428 - 464 Â°F	
Front Barrel Temperature	230 - 250 Â°C	446 - 482 Â°F	
Melt Temperature	240 - 260 Â°C	464 - 500 Â°F	
Mold Temperature	40.0 - 80.0 Â°C	104 - 176 Â°F	
Drying Temperature	80.0 - 90.0 Â°C	176 - 194 Â°F	
Dry Time	2 - 4 hour	2 - 4 hour	
Injection Pressure	68.6 - 108 MPa	9950 - 15600 psi	
Back Pressure	0.689 - 1.38 MPa	100 - 200 psi	
Screw Speed	60 - 80 rpm	60 - 80 rpm	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China