

Samsung Cheil Industries Starex[®] VG-4910 ABS, Glass Filled FR

Category : Polymer , Thermoplastic , ABS Polymer , Acrylonitrile Butadiene Styrene (ABS), 10% Glass Fiber Filled

Material Notes:

Information provided by Samsung Cheil Industries.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Samsung-Cheil-Industries-Starex-VG-4910-ABS-Glass-Filled-FR.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.12 g/cc	1.12 g/cc	ASTM D792
Linear Mold Shrinkage, Flow	0.0010 - 0.0030 cm/cm @Thickness 3.20 mm	0.0010 - 0.0030 in/in @Thickness 0.126 in	ASTM D955
Melt Flow	23 g/10 min @Load 10.0 kg, Temperature 220 Å°C	23 g/10 min @Load 22.0 lb, Temperature 428 Å°F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	109	109	ASTM D785
Tensile Strength at Break	75.5 MPa	11000 psi	5 mm/min; ASTM D638
Tensile Strength, Yield	73.5 MPa	10700 psi	5 mm/min; ASTM D638
Elongation at Break	3.4 %	3.4 %	5 mm/min; ASTM D638
Tensile Modulus	3.73 GPa	540 ksi	5 mm/min; ASTM D638
Flexural Strength	78.5 MPa	11400 psi	2.8 mm/min; ASTM D638
Flexural Modulus	3.63 GPa	526 ksi	2.8 mm/min; ASTM D638
Izod Impact, Notched	0.686 J/cm @Thickness 3.17 mm	1.29 ft-lb/in @Thickness 0.125 in	ASTM D256
	1.18 J/cm @Thickness 6.35 mm	2.20 ft-lb/in @Thickness 0.250 in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	102 Å°C @Thickness 6.40 mm	216 Å°F @Thickness 0.252 in	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	97.0 Å°C @Thickness 6.40 mm	207 Å°F @Thickness 0.252 in	ASTM D648

Thermal Properties Heat Softening Point	Metric °C	English °F	Comments B/120; ISO R306
	101 °C	214 °F	B/120; ISO R306
Flammability, UL94	V-0 @Thickness 1.60 - 3.00 mm	V-0 @Thickness 0.0630 - 0.118 in	
	5VB @Thickness 2.50 mm	5VB @Thickness 0.0984 in	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China