

Samsung Cheil Industries Starex[®] VG-4920 ABS, Glass Filled FR

Category : Polymer , Thermoplastic , ABS Polymer , Acrylonitrile Butadiene Styrene (ABS), 10% Glass Fiber Filled

Material Notes:

Information provided by Samsung Cheil Industries.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Samsung-Cheil-Industries-Starex-VG-4920-ABS-Glass-Filled-FR.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.33 g/cc	1.33 g/cc	ASTM D792
Linear Mold Shrinkage, Flow	0.0010 - 0.0030 cm/cm @Thickness 3.20 mm	0.0010 - 0.0030 in/in @Thickness 0.126 in	ASTM D955
Melt Flow	25 g/10 min @Load 10.0 kg, Temperature 220 Å°C	25 g/10 min @Load 22.0 lb, Temperature 428 Å°F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	110	110	ASTM D785
Tensile Strength, Yield	88.3 MPa	12800 psi	5 mm/min; ASTM D638
Flexural Strength	103 MPa	14900 psi	2.8 mm/min; ASTM D638
Flexural Modulus	5.88 GPa	853 ksi	2.8 mm/min; ASTM D638
Izod Impact, Notched	0.490 J/cm @Thickness 3.17 mm	0.918 ft-lb/in @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	96.0 Å°C @Thickness 6.40 mm	205 Å°F @Thickness 0.252 in	ASTM D648
Flammability, UL94	V-0 @Thickness 1.60 - 3.00 mm	V-0 @Thickness 0.0630 - 0.118 in	
	5VB @Thickness 2.00 - 3.00 mm	5VB @Thickness 0.0787 - 0.118 in	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China