

Samsung Cheil Industries Starex[®] WX-9300 ASA, Unreinforced Heat Resistant

Category : Polymer , Thermoplastic , ASA Polymer , Acrylonitrile/Styrene/Acrylate (ASA), Unreinforced, Molded

Material Notes:

Information provided by Samsung Cheil Industries.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Samsung-Cheil-Industries-Starex-WX-9300-ASA-Unreinforced-Heat-Resistant.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.08 g/cc	1.08 g/cc	ASTM D792
Melt Flow	10 g/10 min @Load 10.0 kg, Temperature 220 Å°C	10 g/10 min @Load 22.0 lb, Temperature 428 Å°F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	105	105	ASTM D785
Tensile Strength, Yield	44.1 MPa	6400 psi	5 mm/min; ASTM D638
Flexural Strength	66.7 MPa	9670 psi	2.8 mm/min; ASTM D638
Flexural Modulus	2.16 GPa	313 ksi	2.8 mm/min; ASTM D638
Izod Impact, Notched	1.86 J/cm @Thickness 3.17 mm	3.49 ft-lb/in @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
Vicat Softening Point	99.0 Å°C	210 Å°F	B/50; ISO R306

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China