

## Samyang Tramid<sup>®</sup> 210P Polyamide, High Productivity

Category : Polymer , Thermoplastic , Nylon

**Material Notes:**

Strong with excellent thermal resistance. Abrasion resistance, chemical resistance and oil resistance are excellent. 210P is a high productivity grade. Applications: Connectors Cable ties Harness clips Tubes Fasteners Castor wheels Hose clips Vacuum hose Hood stay Information provided by Samyang.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Samyang-Tramid-210P-Polyamide-High-Productivity.php](http://www.lookpolymers.com/polymer_Samyang-Tramid-210P-Polyamide-High-Productivity.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.15 g/cc	1.15 g/cc	ASTM D792
Water Absorption	1.4 %	1.4 %	ASTM D570
Linear Mold Shrinkage	0.0080 - 0.016 cm/cm	0.0080 - 0.016 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength	98.1 MPa	14200 psi	ASTM D638
Elongation at Break	6.0 %	6.0 %	ASTM D638
Flexural Yield Strength	113 MPa	16400 psi	ASTM D790
Flexural Modulus	2.79 GPa	405 ksi	ASTM D790
Izod Impact, Notched	0.392 J/cm @Thickness 3.17 mm	0.735 ft-lb/in @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
Melting Point	267 Â°C	513 Â°F	ASTM D3418
Deflection Temperature at 0.46 MPa (66 psi)	233 Â°C	451 Â°F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	92.0 Â°C	198 Â°F	ASTM D648

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China