

Samyang Triloy[®] 200NH PC/ABS alloy, Flame Retardant

Category : Polymer , Thermoplastic , ABS Polymer , Polycarbonate/ABS Alloy, Unreinforced , Polycarbonate (PC)

Material Notes:

Non-halogen
 Characteristics: Impact resistant
 Dimensional stability
 Processability
 Applications: Cellular phone
 Monitor housing
 Coffee maker
 Hair dryer
 O/A part
 All information provided by Samyang

Order this product through the following link:

http://www.lookpolymers.com/polymer_Samyang-Triloy-200NH-PCABS-alloy-Flame-Retardant.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.17 g/cc	1.17 g/cc	ASTM D792
Water Absorption	0.20 %	0.20 %	ASTM D570
	@Time 86400 sec	@Time 24.0 hour	
Linear Mold Shrinkage	0.0050 - 0.0070 cm/cm	0.0050 - 0.0070 in/in	ASTM D955
	@Thickness 3.00 mm	@Thickness 0.118 in	
Melt Flow	25 g/10 min	25 g/10 min	ASTM D1238
	@Load 2.16 kg, Temperature 260 °C	@Load 4.76 lb, Temperature 500 °F	

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	115	115	ASTM D785
Tensile Strength, Yield	58.8 MPa	8530 psi	ASTM D638
Elongation at Break	80 %	80 %	ASTM D638
Flexural Yield Strength	81.4 MPa	11800 psi	ASTM D790
Flexural Modulus	2.26 GPa	327 ksi	ASTM D790
Izod Impact, Unnotched	4.41 J/cm	8.27 ft-lb/in	ASTM D256
	@Thickness 3.17 mm	@Thickness 0.125 in	

Thermal Properties	Metric	English	Comments
CTE, linear	83.0 µm/m-°C	46.1 µin/in-°F	ASTM D696
Deflection Temperature at 1.8 MPa (264 psi)	83.0 °C	181 °F	ASTM D648
Flammability, UL94	V-0	V-0	
	@Thickness 1.59 mm	@Thickness 0.0625 in	

Electrical Properties	Metric	English	Comments
Volume Resistivity	9.00e+16 ohm-cm	9.00e+16 ohm-cm	ASTM D257
Dielectric Constant	3.0 @Frequency 1.00e+6 Hz	3.0 @Frequency 1.00e+6 Hz	ASTM D150
Dielectric Strength	30.0 kV/mm	762 kV/in	ASTM D149
Dissipation Factor	0.0090 @Frequency 1.00e+6 Hz	0.0090 @Frequency 1.00e+6 Hz	ASTM D150
Arc Resistance	120 sec	120 sec	ASTM D495

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	230 - 250 Â°C	446 - 482 Â°F	
Middle Barrel Temperature	220 - 240 Â°C	428 - 464 Â°F	
Front Barrel Temperature	210 - 230 Â°C	410 - 446 Â°F	
Nozzle Temperature	240 - 250 Â°C	464 - 482 Â°F	
Melt Temperature	240 - 250 Â°C	464 - 482 Â°F	
Drying Temperature	120 Â°C	248 Â°F	
Dry Time	3 - 5 hour	3 - 5 hour	
Moisture Content	<= 0.020 %	<= 0.020 %	
Screw Speed	30 - 80 rpm	30 - 80 rpm	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China