

Samyang Triloy[®] 225 PC/ABS alloy

Category : Polymer , Thermoplastic , ABS Polymer , Polycarbonate/ABS Alloy, Unreinforced , Polycarbonate (PC)

Material Notes:

Characteristics: Impact resistant Heat resistant Dimensional stability Applications: Air con. grill All information provided by Samyang

Order this product through the following link:

http://www.lookpolymers.com/polymer_Samyang-Triloy-225-PCABS-alloy.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.13 g/cc	1.13 g/cc	ASTM D792
Water Absorption	0.20 %	0.20 %	ASTM D570
	@Time 86400 sec	@Time 24.0 hour	
Linear Mold Shrinkage	0.0050 - 0.0070 cm/cm	0.0050 - 0.0070 in/in	ASTM D955
	@Thickness 3.00 mm	@Thickness 0.118 in	
Melt Flow	25 g/10 min	25 g/10 min	ASTM D1238
	@Load 5.00 kg, Temperature 250 Â°C	@Load 11.0 lb, Temperature 482 Â°F	

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	118	118	ASTM D785
Tensile Strength, Yield	53.9 MPa	7820 psi	ASTM D638
Elongation at Break	120 %	120 %	ASTM D638
Flexural Yield Strength	78.5 MPa	11400 psi	ASTM D790
Flexural Modulus	1.96 GPa	284 ksi	ASTM D790
Izod Impact, Unnotched	7.85 J/cm	14.7 ft-lb/in	ASTM D256
	@Thickness 3.17 mm	@Thickness 0.125 in	

Thermal Properties	Metric	English	Comments
CTE, linear	73.0 Âµm/m-Â°C	40.6 Âµin/in-Â°F	ASTM D696
Deflection Temperature at 1.8 MPa (264 psi)	116 Â°C	241 Â°F	ASTM D648
Flammability, UL94	HB	HB	
	@Thickness 1.59 mm	@Thickness 0.0625 in	

Electrical Properties	Metric	English	Comments
-----------------------	--------	---------	----------

Electrical Properties	Metric 16 ohm-cm	English 6 ohm-cm	Comments
Dielectric Constant	3.0	3.0	ASTM D150
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	
Dielectric Strength	25.0 kV/mm	635 kV/in	ASTM D149
Dissipation Factor	0.0090	0.0090	ASTM D150
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	
Arc Resistance	123 sec	123 sec	ASTM D495

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	230 - 250 Â°C	446 - 482 Â°F	
Middle Barrel Temperature	220 - 240 Â°C	428 - 464 Â°F	
Front Barrel Temperature	210 - 230 Â°C	410 - 446 Â°F	
Nozzle Temperature	240 - 250 Â°C	464 - 482 Â°F	
Melt Temperature	240 - 250 Â°C	464 - 482 Â°F	
Drying Temperature	120 Â°C	248 Â°F	
Dry Time	3 - 5 hour	3 - 5 hour	
Moisture Content	<= 0.020 %	<= 0.020 %	
Screw Speed	30 - 80 rpm	30 - 80 rpm	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China