

Samyang Trimma[®] SD6320P PMMA, Translucent

Category : Polymer , Thermoplastic , Acrylic (PMMA) , Acrylic, General Purpose, Molded

Material Notes:

High scratch resistance; stability against weak acids, strong acids, weak alkalis and inorganic salts. Information provided by Samyang.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Samyang-Trimma-SD6320P-PMMA-Translucent.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.09 g/cc	1.09 g/cc	ASTM D792
Linear Mold Shrinkage	0.0050 - 0.0070 cm/cm	0.0050 - 0.0070 in/in	ASTM D955
Melt Flow	31 g/10 min	31 g/10 min	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength	49.0 MPa	7110 psi	ASTM D638
Elongation at Break	10 %	10 %	ASTM D638
Flexural Yield Strength	58.8 MPa	8530 psi	ASTM D790
Flexural Modulus	1.86 GPa	270 ksi	ASTM D790
Izod Impact, Notched	0.785 J/cm @Thickness 3.17 mm	1.47 ft-lb/in @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	78.0 Â°C	172 Â°F	ASTM D648
Flammability, UL94	HB @Thickness 1.50 mm	HB @Thickness 0.0591 in	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China