

Samyang Trirex[®] 3000H Polycarbonate, Low-temperature Impact

Category : Polymer , Thermoplastic , Polycarbonate (PC) , Polycarbonate, Impact Modified

Material Notes:

PC is characterized by its excellent impact resistance, dimensional stability and excellent thermal resistance. 3000H is a low temperature impact grade. Applications: Mobile Phone Housing, high gloss. Information provided by Samyang.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Samyang-Trirex-3000H-Polycarbonate-Low-temperature-Impact.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.20 g/cc	1.20 g/cc	ASTM D792
Water Absorption	0.15 %	0.15 %	ASTM D570
Linear Mold Shrinkage	0.0050 - 0.0070 cm/cm	0.0050 - 0.0070 in/in	ASTM D955
Melt Flow	11 g/10 min @Load 1.20 kg, Temperature 300 Â°C	11 g/10 min @Load 2.65 lb, Temperature 572 Â°F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	120	120	ASTM D785
Tensile Strength	61.8 MPa	8960 psi	ASTM D638
Elongation at Break	90 %	90 %	ASTM D638
Flexural Yield Strength	78.5 MPa	11400 psi	ASTM D790
Flexural Modulus	1.91 GPa	277 ksi	ASTM D790
Izod Impact, Notched	8.83 J/cm @Thickness 3.17 mm	16.5 ft-lb/in @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear	60.0 Âµm/m-Â°C	33.3 Âµin/in-Â°F	ASTM D696
Deflection Temperature at 1.8 MPa (264 psi)	127 Â°C	261 Â°F	ASTM D648
Flammability, UL94	HB @Thickness 1.50 mm	HB @Thickness 0.0591 in	

Electrical Properties	Metric	English	Comments
Volume Resistivity	4.00e+16 ohm-cm	4.00e+16 ohm-cm	ASTM D257

Electrical Properties	Metric	English	Comments
Dielectric Strength	30.0 kV/mm	762 kV/in	ASTM D149
Dissipation Factor	0.0090	0.0090	ASTM D150
Arc Resistance	120 sec	120 sec	ASTM D495

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China