

Samyang Trirex[®] 3025N1 Polycarbonate, Flame Retardant

Category : Polymer , Thermoplastic , Polycarbonate (PC) , Polycarbonate, Unreinforced, Flame Retardant

Material Notes:

TRIEX[®] polycarbonate resins offer superior transparency, mechanical properties, good dimensional stability and high electrical performance, which allows it to be widely used for electrical, electronic, appliance, automotive and optical industries. Characteristics: Medium viscosity Self Extinguishing Applications: 1/16 inch UL V-0 All information provided by Samyang

Order this product through the following link:

http://www.lookpolymers.com/polymer_Samyang-Trirex-3025N1-Polycarbonate-Flame-Retardant.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.24 g/cc	1.24 g/cc	ASTM D792
Water Absorption	0.14 %	0.14 %	ASTM D570
	@Time 86400 sec	@Time 24.0 hour	
Linear Mold Shrinkage	0.0050 - 0.0070 cm/cm	0.0050 - 0.0070 in/in	ASTM D955
	@Thickness 3.00 mm	@Thickness 0.118 in	
Melt Flow	11 g/10 min	11 g/10 min	ASTM D1238
	@Load 1.20 kg, Temperature 300 °C	@Load 2.65 lb, Temperature 572 °F	

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	122	122	ASTM D785
Tensile Strength, Yield	66.7 MPa	9670 psi	ASTM D638
Elongation at Break	100 %	100 %	ASTM D638
Flexural Yield Strength	87.3 MPa	12700 psi	ASTM D790
Flexural Modulus	2.26 GPa	327 ksi	ASTM D790
Izod Impact, Unnotched	7.35 J/cm	13.8 ft-lb/in	ASTM D256
	@Thickness 3.17 mm	@Thickness 0.125 in	

Thermal Properties	Metric	English	Comments
CTE, linear	55.0 µm/m-°C	30.6 µin/in-°F	ASTM D696
Deflection Temperature at 0.46 MPa (66 psi)	144 °C	291 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	133 °C	271 °F	ASTM D648

Thermal Properties	V-0 Metric	V-0 English	Comments
	@Thickness 1.59 mm	@Thickness 0.0625 in	

Electrical Properties	Metric	English	Comments
Volume Resistivity	4.00e+16 ohm-cm	4.00e+16 ohm-cm	ASTM D257
Dielectric Constant	2.8	2.8	ASTM D150
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	
Dielectric Strength	30.0 kV/mm	762 kV/in	ASTM D149
Dissipation Factor	0.0082	0.0082	ASTM D150
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	
Arc Resistance	90 sec	90 sec	ASTM D495

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	280 - 300 Â°C	536 - 572 Â°F	
Middle Barrel Temperature	280 - 300 Â°C	536 - 572 Â°F	
Front Barrel Temperature	280 - 300 Â°C	536 - 572 Â°F	
Nozzle Temperature	290 - 310 Â°C	554 - 590 Â°F	
Melt Temperature	300 - 310 Â°C	572 - 590 Â°F	
Drying Temperature	120 Â°C	248 Â°F	
Dry Time	3 - 5 hour	3 - 5 hour	
Moisture Content	<= 0.020 %	<= 0.020 %	
Screw Speed	30 - 80 rpm	30 - 80 rpm	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China