

Samyang Trirex[®] 3026PJ Polycarbonate

Category : Polymer , Thermoplastic , Polycarbonate (PC) , Polycarbonate, Extruded

Material Notes:

PC is characterized by its excellent impact resistance, dimensional stability and excellent thermal resistance.3026PJ is an extrusion grade.Information provided by Samyang.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Samyang-Trirex-3026PJ-Polycarbonate.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.20 g/cc	1.20 g/cc	ASTM D792
Water Absorption	0.15 %	0.15 %	ASTM D570
Linear Mold Shrinkage	0.0050 - 0.0070 cm/cm	0.0050 - 0.0070 in/in	ASTM D955
Melt Flow	2.0 g/10 min @Load 1.20 kg, Temperature 300 Â°C	2.0 g/10 min @Load 2.65 lb, Temperature 572 Â°F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	120	120	ASTM D785
Tensile Strength	73.5 MPa	10700 psi	ASTM D638
Elongation at Break	100 %	100 %	ASTM D638
Flexural Yield Strength	86.3 MPa	12500 psi	ASTM D790
Flexural Modulus	1.96 GPa	284 ksi	ASTM D790
Izod Impact, Notched	7.85 J/cm @Thickness 3.17 mm	14.7 ft-lb/in @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear	50.0 - 70.0 Âµm/m-Â°C	27.8 - 38.9 Âµin/in-Â°F	ASTM D696
Deflection Temperature at 0.46 MPa (66 psi)	137 Â°C	279 Â°F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	132 Â°C	270 Â°F	ASTM D648
Flammability, UL94	V-2 @Thickness 1.50 mm	V-2 @Thickness 0.0591 in	

Electrical Properties	Metric	English	Comments
Volume Resistivity	4.00e+16 ohm-cm	4.00e+16 ohm-cm	ASTM D257
Dielectric Constant	2.85	2.85	ASTM D150
Dielectric Strength	30.0 kV/mm	762 kV/in	ASTM D149
Dissipation Factor	0.0092	0.0092	ASTM D150
Arc Resistance	120 sec	120 sec	ASTM D495

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China