

## Sanyo J-STAT 3180 Antistatic Additive

Category : Other Engineering Material , Additive/Filler for Polymer , Polymer

**Material Notes:**

Information provided by Tomen America, a US distributor of Pelestat.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Sanyo-J-STAT-3180-Antistatic-Additive.php](http://www.lookpolymers.com/polymer_Sanyo-J-STAT-3180-Antistatic-Additive.php)

Physical Properties	Metric	English	Comments
Additive Loading	18 - 23 %	18 - 23 %	to achieve surface resistivity=10 <sup>11</sup> ohms
Melt Flow	70 g/10 min @Load 2.16 kg, Temperature 230 Â°C	70 g/10 min @Load 4.76 lb, Temperature 446 Â°F	ASTM D1238

Thermal Properties	Metric	English	Comments
Melting Point	160 Â°C	320 Â°F	
Maximum Service Temperature, Air	270 Â°C	518 Â°F	Degradation Temp

Electrical Properties	Metric	English	Comments
Surface Resistance	5.00e+9 ohm	5.00e+9 ohm	kept at 23Â°C under 50% R.H.

Descriptive Properties	Value	Comments
Appearance	Pale Yellow Pellet	
Applicable Thermoplastic	PP	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China