

Sax Polymers SAXAMID 126F10 Nylon 6, 50% Glass Fiber

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6, 50% Glass Fiber Filled

Material Notes:

SAXAMID 126F10 is a polyamide 6 injection-molding-grade reinforced with 50% glass fibers. Information provided by SAX Polymers

Order this product through the following link:

http://www.lookpolymers.com/polymer_Sax-Polymers-SAXAMID-126F10-Nylon-6-50-Glass-Fiber.php

Physical Properties	Metric	English	Comments
Density	1.55 g/cc	0.0560 lb/in ³	ISO 1183
Viscosity Test	150 cm ³ /g	150 cm ³ /g	H ₂ O ₄ ; ISO 307

Mechanical Properties	Metric	English	Comments
Tensile Strength	209 MPa	30300 psi	5 mm/min; ISO 527-1
Elongation at Break	3.0 %	3.0 %	5 mm/min; ISO 527-1
Tensile Modulus	15.4 GPa	2230 ksi	1 mm/min; ISO 527-1
Flexural Strength	328 MPa	47600 psi	2 mm/min; ISO 178
Flexural Modulus	11.4 GPa	1650 ksi	2 mm/min; ISO 178
Izod Impact, Notched (ISO)	12.0 kJ/m ²	5.71 ft-lb/in ²	ISO 180/1A
	@Temperature -30.0 °C	@Temperature -22.0 °F	
	14.0 kJ/m ²	6.66 ft-lb/in ²	ISO 180/1A
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Izod Impact, Unnotched (ISO)	82.0 kJ/m ²	39.0 ft-lb/in ²	ISO 180/1U
	@Temperature -30.0 °C	@Temperature -22.0 °F	
	84.0 kJ/m ²	40.0 ft-lb/in ²	ISO 180/1U
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Charpy Impact Unnotched	8.90 J/cm ²	42.4 ft-lb/in ²	ISO 179/1eU
	@Temperature -30.0 °C	@Temperature -22.0 °F	
	9.00 J/cm ²	42.8 ft-lb/in ²	ISO 179/1eU
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Mechanical Properties	Metric	English	Comments
Charpy Impact, Notched	@Temperature -30.0 Â°C	@Temperature -22.0 Â°F	ISO 179/1eA
	1.40 J/cmÂ²	6.66 ft-lb/inÂ²	ISO 179/1eA
	@Temperature 23.0 Â°C	@Temperature 73.4 Â°F	

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	214 Â°C	417 Â°F	80*10*4 s=60mm; ISO 75-1 a
Vicat Softening Point	216 Â°C	421 Â°F	B/120; ISO 306
Flammability, UL94	HB	HB	IEC 60695-11-10
	@Thickness 1.60 mm	@Thickness 0.0630 in	

Processing Properties	Metric	English	Comments
Melt Temperature	260 - 290 Â°C	500 - 554 Â°F	
Mold Temperature	70.0 - 90.0 Â°C	158 - 194 Â°F	
Drying Temperature	80.0 Â°C	176 Â°F	
	@Time 7200 - 21600 sec	@Time 2.00 - 6.00 hour	
Moisture Content	<= 0.20 %	<= 0.20 %	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China