

ScanTube PFA Tubing

Category : Polymer , Thermoplastic , Fluoropolymer , PFA , Polyperfluoroalkoxyethylene, Molded/Extruded

Material Notes:

Information provided by ScanTube, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_ScanTube-PFA-Tubing.php

Physical Properties	Metric	English	Comments
Density	2.15 g/cc	0.0777 lb/in ³	ASTM D792
Water Absorption	<= 0.030 %	<= 0.030 %	ASTM D257

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	60	60	ASTM D2240
Tensile Strength	27.6 MPa	4000 psi	ASTM D638, ASTM D1708
Elongation at Break	300 %	300 %	ASTM D638, ASTM D1708
Tensile Modulus	0.276 GPa	40.0 ksi	ASTM D638
Flexural Modulus	0.689 GPa	100 ksi	ASTM D790
Compressive Strength	15.2 MPa	2200 psi	ASTM D695
Izod Impact, Notched	NB	NB	ASTM D256

Thermal Properties	Metric	English	Comments
Thermal Conductivity	0.187 W/m-K	1.30 BTU-in/hr-ft ² - °F	ASTM C177
Melting Point	305 °C	581 °F	
Maximum Service Temperature, Air	260 °C	500 °F	Continuous
Deflection Temperature at 0.46 MPa (66 psi)	74.0 °C	165 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	48.0 °C	118 °F	ASTM D648
Flammability, UL94	V-0	V-0	
Oxygen Index	>= 95 %	>= 95 %	ASTM D2863

Electrical Properties	Metric	English	Comments
Volume Resistivity	>= 1.00e+18 ohm-cm	>= 1.00e+18 ohm-cm	ASTM D257

Electrical Properties	Metric	English	Comments
Dielectric Constant	@Frequency 1000 Hz	@Frequency 1000 Hz	ASTM D150
	2.1	2.1	ASTM D150
Dielectric Strength	78.7 kV/mm	2000 kV/in	Short Term; 10 mil film; ASTM D149
	0.00020	0.00020	ASTM D150
Dissipation Factor	@Frequency 1000 Hz	@Frequency 1000 Hz	ASTM D150
	0.00030	0.00030	ASTM D150
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	ASTM D150

Descriptive Properties	Value	Comments
Chemical Resistance	Excellent	
Weather Resistance	Excellent	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China