

Schott G018-159 Dental Glass

Category : Ceramic , Glass

Material Notes:

Remarks: Sr- and Zr-containing, high refractive index
 Application: Composite
 Advantages: Greater variety of composition and refractive indices
 Outstanding transparency
 Best radiopacities
 Information Provided by SCHOTT North America, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Schott-G018-159-Dental-Glass.php

Physical Properties	Metric	English	Comments
Density	3.40 g/cc	0.123 lb/in ³	

Thermal Properties	Metric	English	Comments
CTE, linear	8.00 $\mu\text{m}/\text{m}\cdot\text{Å}^\circ\text{C}$ @Temperature -30.0 - 70.0 $\text{Å}^\circ\text{C}$	4.44 $\mu\text{in}/\text{in}\cdot\text{Å}^\circ\text{F}$ @Temperature -22.0 - 158 $\text{Å}^\circ\text{F}$	
Transformation Temperature, Tg	530 $\text{Å}^\circ\text{C}$	986 $\text{Å}^\circ\text{F}$	ISO 7884-8

Optical Properties	Metric	English	Comments
Refractive Index	1.61	1.61	n _d

Component Elements Properties	Metric	English	Comments
Al ₂ O ₃	5.0 %	5.0 %	
B ₂ O ₃	5.0 %	5.0 %	
CaO	5.0 %	5.0 %	
Fluorine, F	2.0 %	2.0 %	
Na ₂ O	5.0 %	5.0 %	
SiO ₂	30 %	30 %	
ZrO ₂	10 %	10 %	

Descriptive Properties	Value	Comments
La ₂ O ₃ (%)	5	
Radiopacity (digital method)	840	ISO 4049
Radiopacity as thickness of aluminium equal to 2-mm thick glass material	6 (300%)	ISO 4049

SrO (%) Descriptive Properties	25 Value	Comments
ZnO (%)	10	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China