

## Schott Glass 8250 Borosilicate Glass

Category : Ceramic , Glass

### Material Notes:

Borosilicate glass for sealing to Kovar metal and molybdenum, electrically highly insulating, low refractive index, good insulator X-ray tubes, transmitting tubes, image amplifier tubes, He-Ne-laser, clad tube for optical fibers, ozone generators The heavy metal content for the elements lead, cadmium, mercury, and hexavalent chromium is below 100 ppm Information provided by SCHOTT AG.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Schott-Glass-8250-Borosilicate-Glass.php](http://www.lookpolymers.com/polymer_Schott-Glass-8250-Borosilicate-Glass.php)

Physical Properties	Metric	English	Comments
Density	2.28 g/cc @Temperature 25.0 Â°C	0.0824 lb/inÂ³ @Temperature 77.0 Â°F	

Mechanical Properties	Metric	English	Comments
Modulus of Elasticity	64.0 GPa	9280 ksi	
Poissons Ratio	0.21	0.21	

Thermal Properties	Metric	English	Comments
CTE, linear	5.00 Âµm/m-Â°C @Temperature 20.0 - 300 Â°C	2.78 Âµin/in-Â°F @Temperature 68.0 - 572 Â°F	ISO 7991
Thermal Conductivity	1.20 W/m-K @Temperature 90.0 Â°C	8.33 BTU-in/hr-ftÂ²- Â°F @Temperature 194 Â°F	
Transformation Temperature, Tg	490 Â°C	914 Â°F	ISO 7884-8
Softening Point	720 Â°C	1330 Â°F	Viscosity 10<sup>7.6</sup> dPa s; ISO 7884-3
Working Point	1055 Â°C	1931 Â°F	Viscosity 10<sup>4</sup> dPa s; ISO 7884-2
Annealing Point	500 Â°C	932 Â°F	Viscosity 10<sup>13</sup> dPa s; ISO 7884-4

Optical Properties	Metric	English	Comments
Refractive Index	1.487 @Wavelength 587.6 nm	1.487 @Wavelength 587.6 nm	

Electrical Properties	Metric	English	Comments
Volume Resistivity	2.00e+8 ohm-cm	2.00e+8 ohm-cm	
	@Temperature 350 Â°C	@Temperature 662 Â°F	
	1.00e+10 ohm-cm	1.00e+10 ohm-cm	
	@Temperature 250 Â°C	@Temperature 482 Â°F	
Dielectric Constant	4.9	4.9	
	@Frequency 1.00e+6 Hz, Temperature 25.0 Â°C	@Frequency 1.00e+6 Hz, Temperature 77.0 Â°F	
Dielectric Loss Index	0.0022	0.0022	
	@Frequency 1.00e+6 Hz, Temperature 25.0 Â°C	@Frequency 1.00e+6 Hz, Temperature 77.0 Â°F	

Chemical Properties	Metric	English	Comments
Acid Class, SR	4	4	DIN 12116
Alkali Class, AR	3	3	ISO 695

Descriptive Properties	Value	Comments
Hydrolytic Resistance	Class HGB 3	ISO 719
Stress-optical Coefficient K (10-6mm2N-1)	3.6	DIN 52314
tk100(Â°C)	375	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China