

Schott Glass 8532 Soft Glass

Category : Ceramic , Glass

Material Notes:

Soft glass, free from Na, of high lead content, lower sealing temperature than glass 8531, high dielectric constant Encapsulation of semiconductor components at low temperature (diodes) Information provided by SCHOTT AG.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Schott-Glass-8532-Soft-Glass.php

Physical Properties	Metric	English	Comments
Density	4.46 g/cc @Temperature 25.0 Â°C	0.161 lb/inÂ³ @Temperature 77.0 Â°F	

Mechanical Properties	Metric	English	Comments
Modulus of Elasticity	56.0 GPa	8120 ksi	
Poissons Ratio	0.24	0.24	

Thermal Properties	Metric	English	Comments
CTE, linear	8.70 Âµm/m-Â°C @Temperature 20.0 - 300 Â°C	4.83 Âµin/in-Â°F @Temperature 68.0 - 572 Â°F	ISO 7991
Thermal Conductivity	0.700 W/m-K @Temperature 90.0 Â°C	4.86 BTU-in/hr-ftÂ²- Â°F @Temperature 194 Â°F	
Transformation Temperature, Tg	435 Â°C	815 Â°F	ISO 7884-8
Softening Point	560 Â°C	1040 Â°F	Viscosity 10^{7.6} dPa s; ISO 7884-3
Working Point	760 Â°C	1400 Â°F	Viscosity 10⁴ dPa s; ISO 7884-2
Annealing Point	430 Â°C	806 Â°F	Viscosity 10¹³ dPa s; ISO 7884-4

Optical Properties	Metric	English	Comments
Refractive Index	1.724 @Wavelength 587.6 nm	1.724 @Wavelength 587.6 nm	

Electrical Properties	Metric	English	Comments
-----------------------	--------	---------	----------

Electrical Properties	2.50e+9 ohm-cm Metric	2.50e+9 ohm-cm English	Comments
	@Temperature 350 Â°C	@Temperature 662 Â°F	
	1.00e+11 ohm-cm	1.00e+11 ohm-cm	
	@Temperature 250 Â°C	@Temperature 482 Â°F	
Dielectric Constant	10.2	10.2	
	@Frequency 1.00e+6 Hz, Temperature 25.0 Â°C	@Frequency 1.00e+6 Hz, Temperature 77.0 Â°F	
Dielectric Loss Index	0.00090	0.00090	
	@Frequency 1.00e+6 Hz, Temperature 25.0 Â°C	@Frequency 1.00e+6 Hz, Temperature 77.0 Â°F	

Chemical Properties	Metric	English	Comments
Acid Class, SR	4	4	DIN 12116
Alkali Class, AR	3	3	ISO 695

Descriptive Properties	Value	Comments
Hydrolytic Resistance	Class HGB 1	ISO 719
Stress-optical Coefficient K (10-6mm2N-1)	1.7	DIN 52314
tk100(Â°C)	440	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China