

## Schott N-BAF4 Glass

Category : Ceramic , Glass

### Material Notes:

Information Provided by SCHOTT North America, Inc.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Schott-N-BAF4-Glass.php](http://www.lookpolymers.com/polymer_Schott-N-BAF4-Glass.php)

| Physical Properties | Metric    | English                  | Comments |
|---------------------|-----------|--------------------------|----------|
| Density             | 2.89 g/cc | 0.104 lb/in <sup>3</sup> |          |

| Mechanical Properties | Metric   | English   | Comments   |
|-----------------------|----------|-----------|------------|
| Knoop Microhardness   | 610      | 610       | .1/20      |
| Modulus of Elasticity | 85.0 GPa | 12300 ksi |            |
| Poissons Ratio        | 0.231    | 0.231     |            |
| Shear Modulus         | 35.0 GPa | 5080 ksi  | calculated |

| Thermal Properties             | Metric   | English   | Comments |
|--------------------------------|--|---|----------|
| CTE, linear                    | 7.20 $\mu\text{m}/\text{m}\cdot\text{Å}^\circ\text{C}$ | 4.00 $\mu\text{in}/\text{in}\cdot\text{Å}^\circ\text{F}$  |          |
|                                | @Temperature -30.0 - 70.0 $\text{Å}^\circ\text{C}$     | @Temperature -22.0 - 158 $\text{Å}^\circ\text{F}$         |          |
|                                | 8.30 $\mu\text{m}/\text{m}\cdot\text{Å}^\circ\text{C}$ | 4.61 $\mu\text{in}/\text{in}\cdot\text{Å}^\circ\text{F}$  |          |
|                                | @Temperature 20.0 - 300 $\text{Å}^\circ\text{C}$       | @Temperature 68.0 - 572 $\text{Å}^\circ\text{F}$          |          |
| Specific Heat Capacity         | 0.740 J/g- $\text{Å}^\circ\text{C}$                    | 0.177 BTU/lb- $\text{Å}^\circ\text{F}$                    |          |
| Thermal Conductivity           | 1.02 W/m-K   | 7.08 BTU-in/hr-ft $\text{Å}^2$ - $\text{Å}^\circ\text{F}$ |          |
| Transformation Temperature, Tg | 580 $\text{Å}^\circ\text{C}$                           | 1080 $\text{Å}^\circ\text{F}$                             |          |

| Optical Properties | Metric               | English              | Comments       |
|--------------------|----------------------|----------------------|----------------|
| Refractive Index   | 1.60568              | 1.60568              | $n_{\text{d}}$ |
|                    | @Wavelength 587.6 nm | @Wavelength 587.6 nm |                |
|                    | 1.60897              | 1.60897              | $n_{\text{e}}$ |
|                    | @Wavelength 546.1 nm | @Wavelength 546.1 nm |                |
|                    | 80.4 %               | 80.4 %               |                |

| Transmission Visible<br>Optical Properties | @Thickness 10.0 mm,<br>Metric<br>Wavelength 380 nm | @Thickness 0.394 in,<br>English<br>Wavelength 380 nm | Comments |
|--|--|--|----------|
|  | 95.9 %   | 95.9 %   |          |
|  | @Thickness 10.0 mm,<br>Wavelength 405 nm           | @Thickness 0.394 in,<br>Wavelength 405 nm            |          |
|  | 98.8 %   | 98.8 %   |          |
|  | @Thickness 10.0 mm,<br>Wavelength 460 nm           | @Thickness 0.394 in,<br>Wavelength 460 nm            |          |
|  | 99.7 %   | 99.7 %   |          |
|  | @Thickness 10.0 mm,<br>Wavelength 580 nm           | @Thickness 0.394 in,<br>Wavelength 580 nm            |          |
|  | 99.8 %   | 99.8 %   |          |
|  | @Thickness 10.0 mm,<br>Wavelength 700 nm           | @Thickness 0.394 in,<br>Wavelength 700 nm            |          |
| IR Transmittance                           | 70.7 %   | 70.7 %   |          |
|  | @Thickness 10.0 mm,<br>Wavelength 2500 nm          | @Thickness 0.394 in,<br>Wavelength 2500 nm           |          |
|  | 99.1 %   | 99.1 %   |          |
|  | @Thickness 10.0 mm,<br>Wavelength 1530 nm          | @Thickness 0.394 in,<br>Wavelength 1530 nm           |          |
| UV Transmittance                           | 1.2 %  | 1.2 %  |          |
|  | @Thickness 10.0 mm,<br>Wavelength 350 nm           | @Thickness 0.394 in,<br>Wavelength 350 nm            |          |
|  | 44.2 %   | 44.2 %   |          |
|  | @Thickness 10.0 mm,<br>Wavelength 365 nm           | @Thickness 0.394 in,<br>Wavelength 365 nm            |          |
|  | 60.1 %   | 60.1 %   |          |
|  | @Thickness 10.0 mm,<br>Wavelength 370 nm           | @Thickness 0.394 in,<br>Wavelength 370 nm            |          |

| Chemical Properties        | Metric | English | Comments |
|----------------------------|--------|---------|----------|
| Acid Class, SR             | 1.0    | 1.0     |          |
| Alkali Class, AR           | 1.2    | 1.2     |          |
| Stain Resistance Class, FR | 0.00   | 0.00    |          |

| Descriptive Properties | Value | Comments |
|------------------------|-------|----------|
| B                      | 1     |          |

| Descriptive Properties     | Value | Comments |
|----------------------------|-------|----------|
| HG                         | 3     |          |
| K (10-6mm <sup>2</sup> /N) | 2.58  |          |
| Phosphate Resistance PR    | 1.3   |          |
| T1013.0 (Å°C)              | 580   |          |
| T107.6 (Å°C)               | 709   |          |

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China