

## Schott N-BAF51 Glass

Category : Ceramic , Glass

### Material Notes:

Information Provided by SCHOTT North America, Inc.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Schott-N-BAF51-Glass.php](http://www.lookpolymers.com/polymer_Schott-N-BAF51-Glass.php)

Physical Properties	Metric	English	Comments
Density	3.33 g/cc	0.120 lb/in <sup>3</sup>	

Mechanical Properties	Metric	English	Comments
Knoop Microhardness	560	560	.1/20
Modulus of Elasticity	91.0 GPa	13200 ksi	
Poissons Ratio	0.262	0.262	
Shear Modulus	36.0 GPa	5220 ksi	calculated

Thermal Properties	Metric	English	Comments
CTE, linear	8.40 $\mu\text{m}/\text{m}\cdot\text{Å}^\circ\text{C}$	4.67 $\mu\text{in}/\text{in}\cdot\text{Å}^\circ\text{F}$	
	@Temperature -30.0 - 70.0 $\text{Å}^\circ\text{C}$	@Temperature -22.0 - 158 $\text{Å}^\circ\text{F}$	
	9.50 $\mu\text{m}/\text{m}\cdot\text{Å}^\circ\text{C}$	5.28 $\mu\text{in}/\text{in}\cdot\text{Å}^\circ\text{F}$	
	@Temperature 20.0 - 300 $\text{Å}^\circ\text{C}$	@Temperature 68.0 - 572 $\text{Å}^\circ\text{F}$	
Specific Heat Capacity	0.840 J/g- $\text{Å}^\circ\text{C}$	0.201 BTU/lb- $\text{Å}^\circ\text{F}$	
Thermal Conductivity	0.670 W/m-K	4.65 BTU-in/hr-ft $\text{Å}^2$ - $\text{Å}^\circ\text{F}$	
Transformation Temperature, Tg	569 $\text{Å}^\circ\text{C}$	1060 $\text{Å}^\circ\text{F}$	

Optical Properties	Metric	English	Comments
Refractive Index	1.65224	1.65224	$n_{\text{d}}$
	@Wavelength 587.6 nm	@Wavelength 587.6 nm	
	1.65569	1.65569	$n_{\text{e}}$
	@Wavelength 546.1 nm	@Wavelength 546.1 nm	
	86.2 %	86.2 %	

Transmission Visible Optical Properties	@Thickness 10.0 mm, Metric Wavelength 380 nm	@Thickness 0.394 in, English Wavelength 380 nm	Comments
	96.3 %	96.3 %	
	@Thickness 10.0 mm, Wavelength 405 nm	@Thickness 0.394 in, Wavelength 405 nm	
	98.8 %	98.8 %	
	@Thickness 10.0 mm, Wavelength 460 nm	@Thickness 0.394 in, Wavelength 460 nm	
	99.7 %	99.7 %	
	@Thickness 10.0 mm, Wavelength 580 nm	@Thickness 0.394 in, Wavelength 580 nm	
	99.7 %	99.7 %	
	@Thickness 10.0 mm, Wavelength 700 nm	@Thickness 0.394 in, Wavelength 700 nm	
IR Transmittance	74.6 %	74.6 %	
	@Thickness 10.0 mm, Wavelength 2500 nm	@Thickness 0.394 in, Wavelength 2500 nm	
	99.2 %	99.2 %	
	@Thickness 10.0 mm, Wavelength 1530 nm	@Thickness 0.394 in, Wavelength 1530 nm	
UV Transmittance	20.9 %	20.9 %	
	@Thickness 10.0 mm, Wavelength 350 nm	@Thickness 0.394 in, Wavelength 350 nm	
	64.2 %	64.2 %	
	@Thickness 10.0 mm, Wavelength 365 nm	@Thickness 0.394 in, Wavelength 365 nm	
	73.9 %	73.9 %	
	@Thickness 10.0 mm, Wavelength 370 nm	@Thickness 0.394 in, Wavelength 370 nm	

Chemical Properties	Metric	English	Comments
Acid Class, SR	5.4	5.4	
Alkali Class, AR	1.3	1.3	
Stain Resistance Class, FR	0.00	0.00	

Descriptive Properties	Value	Comments
B	1	

<b>Descriptive Properties</b>	<b>Value</b>	<b>Comments</b>
HG	5	
K (10-6mm <sup>2</sup> /N)	2.22	
Phosphate Resistance PR	1	
T1013.0 (Å°C)	574	
T107.6 (Å°C)	712	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China