

Schott N-BASF2 Glass

Category : Ceramic , Glass

Material Notes:

Information Provided by SCHOTT North America, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Schott-N-BASF2-Glass.php

Physical Properties	Metric	English	Comments
Density	3.15 g/cc	0.114 lb/in ³	

Mechanical Properties	Metric	English	Comments
Knoop Microhardness	580	580	.1/20
Modulus of Elasticity	84.0 GPa	12200 ksi	
Poissons Ratio	0.247	0.247	
Shear Modulus	34.0 GPa	4930 ksi	calculated

Thermal Properties	Metric	English	Comments
CTE, linear	7.10 $\mu\text{m}/\text{m}\cdot\text{Å}^\circ\text{C}$	3.94 $\mu\text{in}/\text{in}\cdot\text{Å}^\circ\text{F}$	
	@Temperature -30.0 - 70.0 $\text{Å}^\circ\text{C}$	@Temperature -22.0 - 158 $\text{Å}^\circ\text{F}$	
	8.10 $\mu\text{m}/\text{m}\cdot\text{Å}^\circ\text{C}$	4.50 $\mu\text{in}/\text{in}\cdot\text{Å}^\circ\text{F}$	
	@Temperature 20.0 - 300 $\text{Å}^\circ\text{C}$	@Temperature 68.0 - 572 $\text{Å}^\circ\text{F}$	
Specific Heat Capacity	0.660 J/g- $\text{Å}^\circ\text{C}$	0.158 BTU/lb- $\text{Å}^\circ\text{F}$	
Thermal Conductivity	0.940 W/m-K	6.52 BTU-in/hr-ft Å^2 - $\text{Å}^\circ\text{F}$	
Transformation Temperature, Tg	619 $\text{Å}^\circ\text{C}$	1150 $\text{Å}^\circ\text{F}$	

Optical Properties	Metric	English	Comments
Refractive Index	1.66446	1.66446	n _d
	@Wavelength 587.6 nm	@Wavelength 587.6 nm	
	1.66883	1.66883	n _e
	@Wavelength 546.1 nm	@Wavelength 546.1 nm	
	63.4 %	63.4 %	

Transmission Visible Optical Properties	@Thickness 10.0 mm, Wavelength 380 nm Metric	@Thickness 0.394 in, Wavelength 380 nm English	Comments
	91.5 %	91.5 %	
	@Thickness 10.0 mm, Wavelength 405 nm	@Thickness 0.394 in, Wavelength 405 nm	
	98 %	98 %	
	@Thickness 10.0 mm, Wavelength 460 nm	@Thickness 0.394 in, Wavelength 460 nm	
	99.5 %	99.5 %	
	@Thickness 10.0 mm, Wavelength 580 nm	@Thickness 0.394 in, Wavelength 580 nm	
	99.6 %	99.6 %	
	@Thickness 10.0 mm, Wavelength 700 nm	@Thickness 0.394 in, Wavelength 700 nm	
IR Transmittance	85.7 %	85.7 %	
	@Thickness 10.0 mm, Wavelength 2500 nm	@Thickness 0.394 in, Wavelength 2500 nm	
	99.4 %	99.4 %	
	@Thickness 10.0 mm, Wavelength 1530 nm	@Thickness 0.394 in, Wavelength 1530 nm	
UV Transmittance	15.8 %	15.8 %	
	@Thickness 10.0 mm, Wavelength 365 nm	@Thickness 0.394 in, Wavelength 365 nm	
	32.5 %	32.5 %	
	@Thickness 10.0 mm, Wavelength 370 nm	@Thickness 0.394 in, Wavelength 370 nm	

Chemical Properties	Metric	English	Comments
Acid Class, SR	1.0	1.0	
Alkali Class, AR	1.0	1.0	
Stain Resistance Class, FR	0.00	0.00	

Descriptive Properties	Value	Comments
B	1	
Climatic Resistance Test CR	1	
HG	3	

<small>K (10-6mm²/N)</small> Descriptive Properties	<small>3.04</small> Value	Comments
Phosphate Resistance PR	1	
T1013.0 (Å°C)	622	
T107.6 (Å°C)	766	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China