

## Schott N-LAK12 Glass

Category : Ceramic , Glass

### Material Notes:

Information Provided by SCHOTT North America, Inc.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Schott-N-LAK12-Glass.php](http://www.lookpolymers.com/polymer_Schott-N-LAK12-Glass.php)

Physical Properties	Metric	English	Comments
Density	4.10 g/cc	0.148 lb/in <sup>3</sup>	

Mechanical Properties	Metric	English	Comments
Knoop Microhardness	560	560	.1/20
Modulus of Elasticity	87.0 GPa	12600 ksi	
Poissons Ratio	0.288	0.288	
Shear Modulus	34.0 GPa	4930 ksi	calculated

Thermal Properties	Metric	English	Comments
CTE, linear	7.60 $\mu\text{m}/\text{m}\cdot\text{°C}$	4.22 $\mu\text{in}/\text{in}\cdot\text{°F}$	
	@Temperature -30.0 - 70.0 $\text{°C}$	@Temperature -22.0 - 158 $\text{°F}$	
	9.30 $\mu\text{m}/\text{m}\cdot\text{°C}$	5.17 $\mu\text{in}/\text{in}\cdot\text{°F}$	
	@Temperature 20.0 - 300 $\text{°C}$	@Temperature 68.0 - 572 $\text{°F}$	
Transformation Temperature, Tg	614 $\text{°C}$	1140 $\text{°F}$	

Optical Properties	Metric	English	Comments
Refractive Index	1.6779	1.6779	$n_{\text{d}}$
	@Wavelength 587.6 nm	@Wavelength 587.6 nm	
	1.68083	1.68083	$n_{\text{e}}$
	@Wavelength 546.1 nm	@Wavelength 546.1 nm	
Transmission, Visible	94.6 %	94.6 %	
	@Thickness 10.0 mm, Wavelength 380 nm	@Thickness 0.394 in, Wavelength 380 nm	
	97.7 %	97.7 %	

Optical Properties	Metric @Thickness 10.0 mm, Wavelength 405 nm	English @Thickness 0.394 in, Wavelength 405 nm	Comments
	98.7 %	98.7 %	
	@Thickness 10.0 mm, Wavelength 460 nm	@Thickness 0.394 in, Wavelength 460 nm	
	99.6 %	99.6 %	
	@Thickness 10.0 mm, Wavelength 580 nm	@Thickness 0.394 in, Wavelength 580 nm	
	99.7 %	99.7 %	
	@Thickness 10.0 mm, Wavelength 700 nm	@Thickness 0.394 in, Wavelength 700 nm	
IR Transmittance	59.2 %	59.2 %	
	@Thickness 10.0 mm, Wavelength 2500 nm	@Thickness 0.394 in, Wavelength 2500 nm	
	99 %	99 %	
	@Thickness 10.0 mm, Wavelength 1530 nm	@Thickness 0.394 in, Wavelength 1530 nm	
UV Transmittance	3.2 %	3.2 %	
	@Thickness 10.0 mm, Wavelength 310 nm	@Thickness 0.394 in, Wavelength 310 nm	
	46.8 %	46.8 %	
	@Thickness 10.0 mm, Wavelength 334 nm	@Thickness 0.394 in, Wavelength 334 nm	
	91 %	91 %	
	@Thickness 10.0 mm, Wavelength 370 nm	@Thickness 0.394 in, Wavelength 370 nm	

Chemical Properties	Metric	English	Comments
Acid Class, SR	53.3	53.3	
Alkali Class, AR	3.3	3.3	
Stain Resistance Class, FR	1.0	1.0	

Descriptive Properties	Value	Comments
B	1	
Climatic Resistance Test CR	3	
HG	6	

<small>K (10-6mm<sup>2</sup>/N)</small> Descriptive Properties	Value	Comments
Phosphate Resistance PR	4.3	
T1013.0 (°C)	606	
T107.6 (°C)	714	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China